# **Standard Method of Test for**

# **Compressive Strength of Hydraulic Cement Mortar (Using 50-mm or 2-in. Cube Specimens)**

AASHTO Designation: T 106M/T 106-21

**Technically Revised: 2021** 

Editorially Revised: 2021

**Technical Subcommittee: 3a, Hydraulic Cement and Lime** 

ASTM Designation: C109/C109M-21



American Association of State Highway and Transportation Officials 555 12<sup>th</sup> Street NW, Suite 1000 Washington, DC 20004

This is a preview. Click here to purchase the full publication.

# **Compressive Strength of Hydraulic Cement Mortar (Using 50-mm or 2-in. Cube Specimens)**

AASHTO Designation: T 106M/T 106-21

\_\_\_\_\_

AASHO

Technically Revised: 2021

Editorially Revised: 2021

Technical Subcommittee: 3a, Hydraulic Cement and Lime

ASTM Designation: C109/C109M-21

# 1. SCOPE

1.1. This test method covers determination of the compressive strength of hydraulic cement mortar using 50-mm [or 2-in.] cube specimens (see Note 1).

**Note 1**—ASTM C349 provides an alternative procedure for this determination (not to be used for acceptance tests).

- **1.2.** This test method covers the application of the test using either inch-pound or SI units. The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the inch-pound units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.
- 1.3. Values in SI units shall be obtained by measurement in SI units or by appropriate conversion, using the Rules for Conversion and Rebounding given in Standard IEEE/ASTM SI 10, of measurements made in other units.
- 1.4. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.
  Warning—Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure.
- **1.5.** The quality of the results produced by this standard are dependent on the competence of the personnel performing the procedure and the capability, calibration, and maintenance of the equipment used. Agencies that meet the criteria of R 18 are generally considered capable of competent and objective testing/sampling/inspection/etc. Users of this standard are cautioned that compliance with R 18 alone does not completely assure reliable results. Reliable results depend on many factors; following the suggestions of R 18 or some similar acceptable guideline provides a means of evaluating and controlling some of those factors.

## 2. **REFERENCED DOCUMENTS**

- 2.1. *AASHTO Standards*:
  - M 85, Portland Cement
  - M 152M/M 152, Flow Table for Use in Tests of Hydraulic Cement

- M 201, Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes
- M 240M/M 240, Blended Hydraulic Cement
- M 295, Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- M 302, Slag Cement for Use in Concrete and Mortars
- R 18, Establishing and Implementing a Quality Management System for Construction Materials Testing Laboratories
- T 105, Chemical Analysis of Hydraulic Cement
- T 162, Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency

#### 2.2. *ASTM Standards*:

- C91/C91M, Standard Specification for Masonry Cement
- C349, Standard Test Method for Compressive Strength of Hydraulic-Cement Mortars (Using Portions of Prisms Broken in Flexure)
- C670, Standard Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials
- C778, Standard Specification for Standard Sand
- C1005, Standard Specification for Reference Masses and Devices for Determining Mass and Volume for Use in the Physical Testing of Hydraulic Cements
- C1157/C1157M, Standard Performance Specification for Hydraulic Cement
- C1328/C1328M, Standard Specification for Plastic (Stucco) Cement
- C1329/C1329M, Standard Specification for Mortar Cement

#### **2.3**. *IEEE/ASTM Standard*:

■ SI10, American National Standard for Metric Practice

## 3. SUMMARY OF TEST METHOD

3.1. The mortar used consists of one part cement and 2.75 parts of sand proportioned by mass. Portland, air-entraining portland, portland-limestone, or air-entrained portland-limestone cements are mixed at a specified water content. Water content for other cements is that sufficient to obtain a flow of  $110 \pm 5$  in 25 drops of the flow table. Fifty-millimeter [or 2-in.] test cubes are compacted by tamping in two layers. The cubes are cured 24 h in the molds, and then stripped and immersed in lime water until tested.

## 4. SIGNIFICANCE AND USE

4.1. This test method provides a means of determining the compressive strength of hydraulic cement and other mortars, and results may be used to determine compliance with specifications. Further, this test method is referenced by numerous other specifications and test methods. Caution must be exercised in using the results of this test method to predict the strength of concretes.

#### 5. APPARATUS

- 5.1. *Weights and Weighing Devices*—Shall conform to the requirements of ASTM C1005. The weighing device shall be evaluated for precision and accuracy at a total load of 2000 g.
- 5.2. *Glass Graduates*—Of suitable capacities (preferably large enough to measure the mixing water in a single operation) to deliver the indicated volume at 20°C. The permissible variation shall be