
Standard Specification for Corrugated Polyethylene Drainage Pipe

AASHTO Designation: M 252-21

Technically Revised: 2021

Technical Subcommittee: 4b, Flexible and Metallic Pipe



**American Association of State Highway and Transportation Officials
555 12th Street NW, Suite 1000
Washington, DC 20004**

[This is a preview. Click here to purchase the full publication.](#)

Corrugated Polyethylene Drainage Pipe

AASHTO Designation: M 252-21



Technically Revised: 2021

Technical Subcommittee: 4b, Flexible and Metallic Pipe

1. SCOPE

- 1.1. This specification covers the requirements and methods of test for corrugated polyethylene (PE) pipe, couplings, and fittings for use in subsurface drainage systems, storm sewers, and in surface drainage (culverts), where soil support is given to the pipe's flexible walls in all applications.
- 1.1.1. Nominal sizes of 75 to 250 mm (3 to 10 in.) are included.
- 1.1.2. Materials, workmanship, dimensions, pipe stiffness, environmental stress-crack resistance, perforations, joining systems, brittleness, and form of markings are specified.
- Note 1**—When PE pipe is to be used in locations where the ends may be exposed, consideration should be given to combustibility of the PE and the deteriorating effects of prolonged exposure to ultraviolet radiation.
- 1.2. *Units*—The values stated in SI units are to be regarded as standard. Within the text, the U.S. Customary units are shown in parentheses, and may not be exact equivalents.
- 1.3. The following precautionary caveat pertains only to the test method portion, Section 9.3 of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. REFERENCED DOCUMENTS

- 2.1. *ASTM Standards:*
- D618, Standard Practice for Conditioning Plastics for Testing
 - D883, Standard Terminology Relating to Plastics
 - D1693, Standard Test Method for Environmental Stress-Cracking of Ethylene Plastics
 - D2122, Standard Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings
 - D2412, Standard Test Method for Determination of External Loading Characteristics of Plastic Pipe by Parallel-Plate Loading
 - D3350, Standard Specification for Polyethylene Plastics Pipe and Fittings Materials
 - D4218, Standard Test Method for Determination of Carbon Black Content in Polyethylene Compounds by the Muffle-Furnace Technique
 - F667/F667M, Standard Specification for 3 through 24 in Corrugated Polyethylene (PE) Pipe and Fittings
 - F412, Standard Terminology Relating to Plastic Piping Systems

- 2.2. *Federal Standard:*
- Fed. Std. No. 29, CFR 1910.1200 OSHA Hazard Communication Standard; see also Permissible Exposure Limits—Annotated Tables, available at <https://www.osha.gov/dsg/annotated-pels/>

3. TERMINOLOGY

- 3.1. The terminology used in this standard is in accordance with the definitions given in ASTM D883 and ASTM F412 unless otherwise specified.
- 3.2. *buckling*—during pipe flattening testing, any decrease or downward deviation in the pipe load-deflection test curve shall be considered a buckling point.
- 3.3. *crack*—any break or split that extends through the wall or liner.
- 3.4. *crease*—a visible irrecoverable indentation.
- 3.5. *reworked material*—a plastic from a processor's own production that has been reground, pelletized, or solvated after having been previously processed by molding, extrusion, etc. (ASTM D883).
- 3.6. *delamination*—a separation between the liner and outer corrugated wall of Type S pipe as evidenced by a visible gap extending completely through at least one corrugation valley at any point around the circumference of the pipe.
- 3.7. *polyethylene (PE) plastics*—plastics based on polymers made with ethylene as essentially the sole monomer (ASTM D883).

4. CLASSIFICATION

- 4.1. *The corrugated PE pipe covered by this specification is classified as follows:*
- 4.1.1. *Type C*—This pipe shall have a full circular cross section, with a corrugated surface both inside and outside. Corrugations may be either annular or helical.
- 4.1.1.1. *Type CP*—This pipe shall be Type C with Class 2 perforations.
- 4.1.2. *Type S*—This pipe shall have a full circular cross section, with an outer corrugated pipe wall and a smooth inner liner. Corrugations may be either annular or helical. Type S pipe is not available in nominal sizes of less than 100 mm (4 in.).
- 4.1.2.1. *Type SP*—This pipe shall be Type S with either Class 1 or Class 2 perforations.
- 4.2. Class 1 and Class 2 perforations are as described in Sections 7.4.1 and 7.4.2.

5. ORDERING INFORMATION

- 5.1. *Orders using this specification shall include the following information as necessary to adequately describe the desired product:*
- 5.1.1. AASHTO designation and year of issue;