Standard Method of Test for

Measuring Early-Age Compression Strength and Projecting Later-Age Strength

AASHTO Designation: T 276-17 Technical Section: 3c, Hardened Concrete Release: Group 1 (April 2017) ASTM Designation: C918-13



American Association of State Highway and Transportation Officials 444 North Capitol Street N.W., Suite 249 Washington, D.C. 20001

This is a preview. Click here to purchase the full publication.

Measuring Early-Age Compression Strength and Projecting Later-Age Strength

AASHTO Designation: T 276-17



Technical Section: 3c, Hardened Concrete

Release: Group 1 (April 2017)

ASTM Designation: C918-13

1. SCOPE

- 1.1. This test method covers a procedure for making and curing concrete specimens and for testing them at an early age. The specimens are stored under standard curing conditions and the measured temperature history is used to compute a maturity index that is related to strength gain.
- **1.2.** This test method also covers a procedure for using the results of early-age compressive-strength tests to project the potential strength of concrete at later ages.
- **1.3.** The values stated in SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore; each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.
- **1.4.** The text of this standard references notes and footnotes that provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.
- **1.5.** This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. **REFERENCED DOCUMENTS**

- 2.1. *AASHTO Standards*:
 - M 205M/M 205, Molds for Forming Concrete Test Cylinders Vertically
 - R 39, Making and Curing Concrete Test Specimens in the Laboratory
 - R 60, Sampling Freshly Mixed Concrete
 - T 22, Compressive Strength of Cylindrical Concrete Specimens
 - T 23, Making and Curing Concrete Test Specimens in the Field
 - T 231, Capping Cylindrical Concrete Specimens

2.2. *ASTM Standards*:

■ C1074, Standard Practice for Estimating Concrete Strength by the Maturity Method

- C1231/C1231M, Standard Practice for Use of Unbonded Caps in Determination of Compressive Strength of Hardened Concrete Cylinders
- C1768/C1768M, Standard Practice for Accelerated Curing of Concrete Cylinders

3. TERMINOLOGY

- **3.1**. *Definitions*:
- **3.1.1.** Refer to ASTM C1074 for the definition of the following terms: datum temperature, equivalent age, maturity, maturity function, maturity index, and temperature–time factor.
- **3.2**. *Definition of Terms Specific to This Standard*:
- **3.2.1**. *potential strength*—the strength of a test specimen that would be obtained at a specified age under standard curing conditions.
- **3.2.2**. *prediction equation*—the equation representing the straight-line relationship between compressive strength and the logarithm of the maturity index.
- **3.2.2.1.** *Discussion*—The prediction equation is used to project the strength of a test specimen based upon its measured early-age strength. The general form of the prediction equation used in this test method is:

$$S_M = S_m + b \left(\log M - \log m \right) \tag{1}$$

where:

- S_M = predicted strength at maturity index, M;
- S_m = measured compressive strength at maturity index, m;
- b = slope of the line;
- M = maturity index under standard curing conditions; and
- m = maturity index of the specimen tested at early age.

The prediction equation is developed by performing compressive strength tests at various ages, computing the corresponding maturity indices at the test ages, and plotting the compressive strength as a function of the logarithm of the maturity index. A best-fit line is drawn through the data and the slope of this line is used in the prediction equation.

3.2.3. *projected strength, n*—the potential strength estimated by using the measured early-age strength and the previously established prediction equation.

4. SUMMARY OF TEST METHOD

- 4.1. Cylindrical test specimens are prepared and cured in accordance with the appropriate section of T 23 or in accordance with R 39. The temperature of a representative specimen is monitored during the curing period. Specimens are tested for compressive strength at an early age beyond 24 h, and the concrete temperature history is used to compute the maturity index at the time of test.
- 4.2. A procedure is presented for acquiring a series of compressive strength values and the corresponding maturity indices at different ages. These data are used to develop a prediction equation that is used subsequently to project the strengths at later ages based upon measured early-age strengths.

)