
Standard Specification for

**Uncoated, Corrosion-Resistant,
Deformed and Plain Chromium
Alloyed, Billet-Steel Bars
for Concrete Reinforcement
and Dowels**

AASHTO Designation: M 334M/M 334-17¹

Technical Section: 4f, Metals

Release: Group 2 (June 2017)



**American Association of State Highway and Transportation Officials
444 North Capitol Street N.W., Suite 249
Washington, D.C. 20001**

Uncoated, Corrosion-Resistant, Deformed and Plain Chromium Alloyed, Billet-Steel Bars for Concrete Reinforcement and Dowels

AASHTO Designation: M 334M/M 334-17¹



Technical Section: 4f, Metals

Release: Group 2 (June 2017)

1. SCOPE

- 1.1. This specification covers uncoated, corrosion-resistant, deformed and plain chromium alloyed, billet-steel concrete reinforcement and dowel bars in cut lengths or coils (Notes 1 and 2). The standard sizes and dimensions of deformed bars and their number designations shall be those listed in Table 2 for millimeter-kilogram bars [Table 3 for inch-pound bars].
- Note 1**—For coils of deformed bars, the capacity of industrial equipment limits the maximum bar size that can be straightened.
- Note 2**—The degree of corrosion resistance specified for both concrete reinforcement and dowel bars is typically dependent on the type of structure, the expected in-service environmental conditions, and the material properties of the concrete in which they are embedded.
- 1.2. Bars are of three minimum yield levels: 420 MPa [60,000 psi], 550 MPa [80,000 psi], and 690 MPa [100,000 psi], designated as Grade 420 [60], Grade 550 [80], and Grade 690 [100], respectively.
- 1.3. Hot-rolled plain rounds, in sizes up to and including 57 mm [2.25 in.] in diameter in coils or cut lengths, when specified for dowels, spirals, and structural ties or supports, shall be furnished under this specification in Grade 420 [60], Grade 550 [80], and Grade 690 [100] (Note 3).
- For ductility properties, test provisions of the nearest nominal diameter deformed bar size shall apply. Those requirements providing for deformations and marking shall not be applicable (Note 3).
- Note 3**—The weight for plain rounds smaller than 10 mm [$\frac{3}{8}$ in.] in diameter shall be computed on the basis of the size in ASTM A510/A510M.
- Note 4**—When welding of the material listed in this specification is required, it should be in conformance with AWS D1.4 *Structural Welding Code—Reinforcing Steel* and the applicable sections of AWS D1.6 *Structural Welding Code—Stainless Steels*. If the material is not addressed in these specifications, the manufacturer of the steel should be contacted to obtain a welding procedure for the particular application.
- 1.4. This specification is applicable for orders in either SI units (as M 334M) or in inch-pound units (as M 334). SI units and inch-pound units are not necessarily equivalent. Inch-pound units are shown in brackets in the text for clarity, but they are the applicable values when the material is ordered to M 334.

2. REFERENCED DOCUMENTS

2.1. *AASHTO Standards:*

- T 244, Mechanical Testing of Steel Products
- T 285, Bend Test for Bars for Concrete Reinforcement
- T 372M/T 372, Sensitivity of Stainless Steel to Intergranular Attack
- T 373M/T 373, Comparative Qualitative Corrosion Characterization of Steel Bars Used for Concrete Reinforcement (Linear Polarization Resistance and Potentiodynamic Polarization Tests)
- T 374M/T 374, Comparative Qualitative Corrosion Characterization of Uncoated Chromium-Alloyed Steel Bars Used in Concrete Reinforcement (Tombstone Test)
- T 375M/T 375, Identification of Iron-Based Alloy Steel Bars for Concrete Reinforcement or Dowels by Handheld X-Ray Fluorescence (XRF) Spectrometer
- T 376M/T 376, Macrocell Slab Chloride Threshold

2.2. *ASTM Standards:*

- A276/A276M, Standard Specification for Stainless Steel Bars and Shapes
- A484/A484M, Standard Specification for General Requirements for Stainless Steel Bars, Billets, and Forgings
- A510/A510M, Standard Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel, and Alloy Steel
- A700, Standard Guide for Packaging, Marking, and Loading Methods for Steel Products for Shipment
- A751, Standard Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products
- A955/A955M, Standard Specification for Deformed and Plain Stainless-Steel Bars for Concrete Reinforcement
- A1035/A1035M, Standard Specification for Deformed and Plain, Low-Carbon, Chromium, Steel Bars for Concrete Reinforcement
- E29, Standard Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

2.3. *Military Standards:*

- MIL-STD-129, Marking for Shipment and Storage
- MIL-STD-163, Steel Mill Products Preparation for Shipment and Storage

2.4. *Federal Standard:*

- Fed. Std. No. 123, Marking for Shipment (Civil Agencies)

2.5. *AWS Standards:*

- AWS D1.4, *Structural Welding Code—Reinforcing Steel*
- AWS D1.6, *Structural Welding Code—Stainless Steels*

3. TERMINOLOGY

3.1. *Description of Terms Specific to This Standard:*