Standard Method of Test for

Nonrepetitive Static Plate Load Test of Soils and Flexible Pavement Components for Use in Evaluation and Design of Airport and Highway Pavements

AASHTO Designation: T 222-81 (2017)

Technical Section: 1b, Geotechnical Exploration, Instrumentation, Stabilization, and Field Testing

Release: Group 3 (August 2017)



American Association of State Highway and Transportation Officials 444 North Capitol Street N.W., Suite 249 Washington, D.C. 20001

This is a preview. Click here to purchase the full publication.

Standard Method of Test for

Nonrepetitive Static Plate Load Test of Soils and Flexible Pavement Components for Use in Evaluation and Design of Airport and Highway Pavements

AASHTO Designation: T 222-81 (2017)



Technical Section: 1b, Geotechnical Exploration, Instrumentation, Stabilization, and Field Testing

Release: Group 3 (August 2017)

1.	SCOPE	
1.1.	This method covers the making of nonrepetitive static plate load test on subgrade soils and flexible pavement components, in either the compacted condition or the natural state, and is intended to provide data for use in the evaluation and design of rigid and flexible-type airport and highway pavements.	
1.2.	The values stated in SI units are to be regarded as the standard.	
2.	TERMINOLOGY	
2.1.	Definitions:	
2.1.1.	<i>deflection</i> —the amount of downward vertical movement of a surface due to the application of a load to the surface.	
2.1.2.	<i>residual deflection</i> —the difference between original and final elevations of a surface resulting from the application and removal of one or more loads to and from the surface.	
2.1.3.	<i>rebound deflection</i> —the amount of vertical rebound of a surface that occurs when a load is removed from the surface.	
3.	APPARATUS	
3.1.	<i>Field Test Apparatus</i> —The required field test apparatus, part of which is shown in Figure 1, is as follows:	
3.1.1.	<i>Loading Device</i> —A truck or trailer, or a combination of both, a tractor trailer, an anchored frame or other structure loaded with sufficient mass to produce the desired reaction on the surface under test. The supporting points (wheels in the case of a truck or trailer) shall be at least 2.4 m (8 ft) from the circumference of the largest diameter bearing plate being used. The dead load shall be at least 5675 kg (25,000 lb).	

3.1.2. *Hydraulic Jack Assembly*—With a spherical bearing attachment, capable of applying and releasing the load in increments. The jack shall have sufficient capacity for applying the maximum load required and shall be equipped with an accurately calibrated gauge, or proving ring, that will indicate the magnitude of the applied load.



Figure 1—Plate Bearing Test Equipment

3.1.3. *Bearing Plate*—A set of circular steel bearing plates not less than 25.4 mm (1 in.) in thickness, machined so that they can be arranged in pyramid fashion to ensure rigidity, and have diameters ranging from 152 to 762 mm (6 to 30 in.). The diameters of adjacent plates in the pyramid arrangement shall not differ by more than 152 mm (6 in.) (Note 1). Aluminum alloy No. 24ST plates 38 mm (1.50 in.) thick may be used in lieu of steel plates.

TS-1b	T 222-2	AASHTO
	This is a preview. Click here to purchase the full publication.	