Guide to Hot Weather Concreting

Reported by ACI Committee 305

ACI 305R-20



American Concrete Institute Always advancing

This is a preview. Click here to purchase the full publication.



American Concrete Institute Always advancing First Printing September 2020 ISBN: 978-1-64195-112-8

Guide to Hot Weather Concreting

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at http://concrete.org/Publications/ DocumentErrata.aspx. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided "as is" without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised the ACI Collection of Concrete Codes, Specifications, and Practices.

American Concrete Institute 38800 Country Club Drive Farmington Hills, MI 48331 Phone: +1.248.848.3700 Fax: +1.248.848.3701

www.concrete.org

This is a preview. Click here to purchase the full publication.

ACI 305R-20

Guide to Hot Weather Concreting

Reported by ACI Committee 305

Oscar R. Antommattei, Chair

James M. Aldred Godwin Q. Amekuedi Mehdi Bakhshi Philip Brandt Kirk K. Deadrick Michael S. Faubel Antonio J. Guerra G. Terry Harris T. J. Harris Kenneth C. Hover Tarek S. Khan Frank A. Kozeliski

Consulting Members

D. Gene Daniel*

Chad B. Hensley, Secretary

Bruce G. Smith William W. Squyres Boris Y. Stein Diep T. Tu

George V. Teodoru

James N. Cornell

*Deceased.

Environmental factors, such as high ambient temperature, low humidity, high wind, or both low humidity and high wind, affect concrete properties and the construction operations of mixing, transporting, and placing of the concrete materials. This guide provides measures that can be taken to minimize the undesirable effects of these environmental factors and reduce the potential for serious problems.

This guide defines hot weather, discusses potential problems, and presents practices intended to minimize them. These practices include selecting materials and proportions, precooling ingredients, and batching. Other topics discussed include length of haul, consideration of concrete temperature as placed, facilities for handling concrete at the site, and, during the early curing period, placing and curing techniques, and appropriate testing and inspection procedures in hot weather conditions.

The materials, processes, quality control measures, and inspections described in this document should be tested, monitored, or performed as applicable only by individuals holding the appropriate ACI certifications or equivalent.

Keywords: air entrainment; cooling; curing; evaporation; high temperature; hot weather construction; plastic shrinkage; production methods; retempering; slump tests; water content.

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer. CONTENTS

CHAPTER 1—INTRODUCTION AND SCOPE, p. 2

1.1—Introduction, p. 2

Darmawan Ludirdja

Quinn McGuire

David R. Nau

William D. Palmer

Jonathan L. Poole

Jorge L. Quiros

1.2—Scope, p. 2

CHAPTER 2—NOTATION AND DEFINITIONS, p. 2

- 2.1—Notation, p. 2
- 2.2—Definitions, p. 3

CHAPTER 3—POTENTIAL PROBLEMS AND PRACTICES, p. 3

- 3.1—Potential problems in hot weather, p. 3
- 3.2—Potential problems related to other factors, p. 3
- 3.3—Practices for hot weather concreting, p. 3

CHAPTER 4—EFFECTS OF HOT WEATHER ON CONCRETE PROPERTIES, p. 4

- 4.1—General, p. 4
- 4.2—Calculating estimated evaporation rate, p. 7
- 4.3—Effects of temperature of concrete, p. 9
- 4.4—Maximum ambient and concrete temperature, p. 9
- 4.5—Water, p. 10
- 4.6-Cement, p. 11
- 4.7—Supplementary cementitious materials, p. 12
- 4.8—Chemical admixtures, p. 12
- 4.9-Aggregates, p. 14
- 4.10-Fibers, p. 14
- 4.11—Proportioning, p. 15

ACI 305R-20 was adopted and published September 2020.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing

Copyright © 2020, American Concrete Institute.

CHAPTER 5—PRODUCTION AND DELIVERY, p. 16

- 5.1—General, p. 16
- 5.2—Temperature control of concrete, p. 16
- 5.3—Batching and mixing, p. 17
- 5.4—Delivery, p. 18
- 5.5-Slump adjustment, p. 18
- 5.6—Properties of concrete mixtures, p. 18
- 5.7—Retempering, p. 18

CHAPTER 6—PLACING AND CURING, p. 18

- 6.1—General, p. 18
- 6.2-Preparations for placing and curing, p. 18
- 6.3-Placement and finishing, p. 19
- 6.4—Curing and protection, p. 20

CHAPTER 7—TESTING AND INSPECTION, p. 21

- 7.1—Testing, p. 21
- 7.2-Inspection, p. 21

CHAPTER 8—REFERENCES, p. 22

8.1—Referenced standards and reports, p. 22 8.2—Cited references, p. 23

APPENDIX A—ESTIMATING CONCRETE TEMPERATURE, p. 25

A.1—Estimating temperature of freshly mixed concrete, p. 25

A.2—Estimating temperature of concrete with ice, p. 25

APPENDIX B—METHODS FOR COOLING FRESH CONCRETE, p. 25

- B.1—Cooling with chilled mixing water, p. 25
- B.2—Liquid nitrogen cooling of mixing water, p. 25
- B.3—Cooling concrete with ice, p. 25
- B.4—Cooling mixed concrete with liquid nitrogen, p. 26
- B.5-Cooling of coarse aggregates, p. 26

CHAPTER 1—INTRODUCTION AND SCOPE

1.1—Introduction

Hot weather can create problems in delivery, mixing, placing, and curing hydraulic-cement concrete that can adversely affect the properties and serviceability of the concrete. Most of these problems relate to the increased rate of cement hydration at higher temperature and increased evaporation rate of moisture from the freshly mixed concrete. The rate of cement hydration depends on ambient and concrete temperature, cement composition and fineness, amount and type of supplementary cementitious materials, and admixtures used.

A maximum as-placed concrete temperature is often specified in an effort to control rate of setting, strength, durability, plastic shrinkage cracking, thermal cracking, and drying shrinkage. The placement of concrete in hot weather, however, is too complex to be dealt with by just setting a maximum as-placed or as-delivered concrete temperature. Concrete durability is defined as the ability of concrete to resist weathering action, chemical attack, abrasion, or any other process of deterioration (ACI 201.2R). Generally, if concrete strengths are satisfactory and curing practices are sufficient to avoid undesirable drying of surfaces, the durability of hot weather concrete will not differ greatly from similar concrete placed at normal temperatures.

Where an acceptable record of field tests is not available, concrete proportions can be determined by trial batches (ACI 301 and 211.1). Trial batches should be made at temperatures anticipated in the work and mixed following one of the procedures described in 4.10. The concrete supplier is generally responsible for determining concrete proportions to produce the required quality of concrete unless specified otherwise.

If the initial 24-hour curing is at 100°F (38°C), the 28-day compressive strength of the test specimens may be 10 to 15 percent lower than if cured at the required ASTM C31/C31M curing temperature (Gaynor et al. 1985). If the cylinders are allowed to dry at early ages, strengths will be reduced even further (Cebeci 1987). Therefore, proper curing of the test specimens during hot weather is critical, and steps should be taken to ensure that the specified procedures are followed.

The effects of high air temperature and low relative humidity are more pronounced with increases in wind speed. The potential problems of hot weather concreting can occur at any time of the year, but generally occur during the summer season. Drying conditions can occur even at lower ambient temperatures, with slower set times, lower relative humidity, and wind, all of which are conducive to higher evaporation. Precautionary measures required on a windy, sunny day will be stricter than those required on a calm, humid day, even if air temperatures are identical.

1.2—Scope

This guide identifies problems associated with hot weather concreting and describes practices that alleviate these potential adverse effects. These practices include suggested preparations and procedures for use in general types of hot weather construction, such as pavements, bridges, and buildings either cast in place or precast. Temperature, volume changes, and cracking problems associated with mass concrete are treated more thoroughly in ACI 207.1R, 207.2R, and 224R.

CHAPTER 2—NOTATION AND DEFINITIONS

2.1—Notation

 $E = \text{evaporation rate, } lb/ft^2/h (kg/m^2/h)$

 e_a = water vapor pressure in psi (mmHg) in the air surrounding the concrete obtained by multiplying the saturation vapor pressure at the temperature of the air surrounding the concrete by the relative humidity of the air. Air temperature and relative humidity are measured approximately 4 to 6 ft (1.2 to 1.8 m) above the concrete surface on the windward side and shielded from the sun's rays

 e_o = saturation water vapor pressure in psi (mmHg) in the air immediately over the concrete surface, at the concrete temperature.

- e_s = saturation vapor pressure, psi (kPa)
- r = relative humidity, percent



This is a preview. Click here to purchase the full publication.