
An ACI Technical Publication

SYMPOSIUM VOLUME



Materials, Analysis, Structural Design and Applications of Textile Reinforced Concrete/Fabric Reinforced Cementitious Matrix

SP-345

Editors:

Barzin Mobasher and Flávio de Andrade Silva





Materials, Analysis, Structural Design and Applications of Textile Reinforced Concrete/Fabric Reinforced Cementitious Matrix

Sponsored by ACI Committee 549, Rilem-MCC

The Concrete Convention and Exposition October 20-24, 2019 Cincinnati, OH, USA

Editors: Barzin Mobasher and Flávio de Andrade Silva



First printing, February 2021

Discussion is welcomed for all materials published in this issue and will appear ten months from this journal's date if the discussion is received within four months of the paper's print publication. Discussion of material received after specified dates will be considered individually for publication or private response. ACI Standards published in ACI Journals for public comment have discussion due dates printed with the Standard.

The Institute is not responsible for the statements or opinions expressed in its publications. Institute publications are not able to, nor intended to, supplant individual training, responsibility, or judgment of the user, or the supplier, of the information presented.

The papers in this volume have been reviewed under Institute publication procedures by individuals expert in the subject areas of the papers.

Copyright © 2021 AMERICAN CONCRETE INSTITUTE 38800 Country Club Dr. Farmington Hills, Michigan 48331

All rights reserved, including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by any electronic or mechanical device, printed or written or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

Printed in the United States of America

Editorial production: Gail L. Tatum

ISBN-13: 978-1-64195-133-3

This is a preview. Click here to purchase the full publication.

PREFACE

Materials, Analysis, Structural Design and Applications of Textile Reinforced Concrete/Fabric Reinforced Cementitious Matrix

Several state-of-the-art sessions on textile-reinforced concrete/fabric-reinforced cementitious matrix (TRC/FRCM) were organized by ACI Committee 549 in collaboration with RILEM TC MCC during the ACI Fall 2019 Convention in Cincinnati, OH, and the ACI Virtual Technical Presentations in June 2020. The forum provided a unique opportunity to collect information and present knowledge in the field of TRC and FRCM as sustainable construction materials. The term TRC is typically used for new construction applications whereas the term FRCM refers to the repair applications of existing concrete and masonry. Both methods use a textile mesh as reinforcement and a cementitious-based matrix component and, due to high tensile and flexural strength and ductility, can be used to support structural loads. The technical sessions aimed to promote the technology, and document and develop recommendations for testing, design, and analysis, as well as to showcase the key features of these ductile and strong cement composite systems. New methods for characterization of key parameters were presented, and the results were collected towards the development of technical and state-of-the-art papers. Textile types include polymer-based (low and high stiffness), glass, natural, basalt, carbon, steel, and hybrid, whereas the matrix can include cementitious, geopolymers, and lightweight matrix (aggregates). Additives such as short fibers, fillers, and nanomaterials were also considered.

The sessions were attended by researchers, designers, students, and participants from the construction and fiber industries. The presence of people with different expertise and from different regions of the world provided a unique opportunity to share knowledge and promote collaborative efforts. The experience of an online technical forum was a success and may be used for future opportunities.

The workshop technical sessions chairs sincerely thank the ACI staff for doing a wonderful job in organizing the virtual sessions and ACI TC 549 and Rilem TC MCC for the collaboration.

August 2020 Barzin Mobasher Flávio de Andrade Silva



TABLE OF CONTENTS

SP-345-1: Carbon Reinforced Concrete Under Cyclic Tensile Loading Authors: Arne Spelter, Juliane Wagner, Manfred Curbach, and Josef Hegger	1-15
SP-345-2: Shear Capacity of TRC slabs: Modelling and Examples from Practice	16-31
SP-345-3: Performance of TRM/TRC systems under elevated temperatures and fire conditions Authors: Catherine (Corina) Papanicolaou and Thanasis Triantafillou	32-46
SP-345-4: Staircase system made of carbon reinforced concrete (CRC) Authors: Egbert Müller and Manfred Curbach	47-58
SP-345-5: Experimental Approach to Determine Lap Splice Length of Textile Reinforced Concrete Members Subjected to Tensile Force	59-68
SP-345-6: Numerical modeling of FRCM composites for the seismic retrofitting of existing concrete structures	69-85
SP-345-7: Effect of Bonded Length on Material Characterization of FRCM Composites Authors: Houman Hadad, Davide Campanini, and Antonio Nanni	86-101
SP-345-8: FRCM confined reinforced concrete columns: experimental behavior and modeling	102-116
SP-345-9: On the tensile behavior of high-strength strain-hardening cement-based composites (SHCC) reinforced with carbon textile – influence of yarn-SHCC bon	117-127
SP-345-10: Development and design of smart textile reinforcement for concrete pipes Authors: Goezdem Dittel, Kira Heins, and Thomas Gries	128-142
SP-345-11: Design Formulas for FRCM Strengthened Masonry Elements Under Compression or Shear Load	143-155
SP-345-12: Investigation on End-Anchorage of SRG Composites Externally Bonded to a Concrete Substrate	156-168
SP-345-13: Shear strengthening of reinforced concrete T-beams using carbon reinforced concrete Authors: Sarah Bergmann, Sebastian May, Josef Hegger, and Manfred Curbach	169-184

SP-345-14: Influence of the test set-up on the bond behavior of FRCM composites	5-195
SP-345-15: Flexural Behavior of Carbon Fiber Textile-Reinforced Concrete I-Section Beams196 Authors: Kissila Botelho Goliath, Daniel C. T. Cardoso, and Flavio de A. Silva	-206
SP-345-16: An Overview of The Tensile and Bond Behavior of Fabric Reinforced Cementitious Matrix (FRCM) Composites	'-220
SP-345-17: Utility of Glass and Carbon Fabrics in Ultra High-Performance Cementitious Matrices	I-229
SP-345-18: Correlation of Tensile and Flexural Response of Continuous Polypropylene Fiber Reinforced Cement Composites)-242
SP-345-19: Flexural strengthening of RC slabs with CRC and the influence of the positional accuracy243 Authors: Egbert Müller, Sarah Bergmann, Manfred Curbach, and Josef Hegger	3-257

SP-345: Materials, Analysis, Structural Design and Applications of Textile Reinforced Concrete/Fabric Reinforced Cementitious Matrix

CARBON REINFORCED CONCRETE UNDER CYCLIC TENSILE LOADING

Arne Spelter, Juliane Wagner, Manfred Curbach and Josef Hegger

Synopsis: Carbon reinforced concrete (CRC) is a material composed of a high-performance concrete and a carbon reinforcement (textile grids, lamellas, rods). Composite materials with reinforcements of other fiber materials are called textile reinforced concrete (TRC). The investigations of CRC started more than 20 years ago and the continuous development as well as research findings have opened many fields of application. Today, the use of CRC includes the strengthening of reinforced concrete elements as well as the realization of new elements such as facades, shells and even bridges.

Some of these structures require knowledge of the fatigue behavior due to cyclic loading (e. g. bridges). In a collaborative project of the Institute of Structural Concrete of the RWTH Aachen University and the Institute of Concrete Structures of the TU Dresden, the uniaxial tensile fatigue behavior of two carbon textile reinforcement types was systematically investigated. The specimens were subjected up to 107 loading cycles and stress ranges up to 261 ksi (1,800 MPa). The influence of the maximum load and amplitude were investigated as well as fatigue curves for these two reinforcement types derived.

<u>Keywords:</u> Carbon reinforced concrete (CRC), cyclic loading, fatigue curve, S-N curve, tensile fatigue, textile reinforced concrete (TRC)

This is a preview. Click here to purchase the full publication.

Author's Biographies:

Arne Spelter is a research associate at the Institute of Structural Concrete at the RWTH Aachen University, Germany. He received his BS and MS from the RWTH Aachen University in 2014 and 2016. Within the scope of his research work he deals with the static and dynamic long-term behavior of non-metallic reinforcements.

Juliane Wagner is a research associate at the Institute of Concrete Structures, Technische Universität (TU) Dresden, Germany. She received her Dipl.-Ing. degree from TU Dresden in 2015. Her research interests include material behavior of textile reinforced concrete under quasi-static and cyclic load.

ACI member **Manfred Curbach** is the director of the Institute of Concrete Structures, TU Dresden. He studied at the TU Dortmund University until 1982 and received his doctoral degree in 1987 from Karlsruhe University, Germany. Manfred Curbach is university professor since 1994. His research interests include e.g. the mechanical behavior of concrete and textile reinforced concrete under multiaxial, dynamical or impact loading, as well as the repair and strengthening of old concrete structures with textile reinforced concrete.

Josef Hegger is professor of the Institute of Structural Concrete at the RWTH Aachen University since 1993. He is part of several standard committees for the Eurocode 2 – Design of Concrete Structures. In addition, he is a member of several committees of experts of the Deutsches Institut für Bautechnik (DIBt). His research interests include the use of novel reinforcement elements and materials such as carbon in addition to the conventional areas of building and bridge constructions in typical steel reinforced concrete design.

1. Introduction

For more than two decades the innovative composite materials textile and carbon reinforced concrete (TRC and CRC), which comprise reinforcements as textile grids, bars, and lamellas, have been investigated. As a result, extensive knowledge about fibers, impregnation materials and the composite material as well as about their testing methods has been gathered [1-13].

The continuous development of non-metallic reinforcements, especially of grids and bars, paved the way for the realization of several structures made of CRC including facades, shells, slab elements and even bridges [14-21]. Recent research projects show, in addition to the already known designs for foot and cycle path bridges, the applicability of the reinforcements for road bridges [22, 23]. Another innovative field of application is the strengthening of existing structures with thin layers of CRC. Especially the strengthening of the shear capacity is interesting for the future regarding the current shear problems in case of bridges [24, 25]. Here, the fatigue behavior is of great importance and requires the examination of the textile reinforcements for fatigue.

Only a few investigations on the fatigue behavior of textile grids are available, e. g. [26-28]. However, these were primarily intended to provide knowledge of the basic applicability under cyclic loading conditions. Wagner and Curbach recently started systematic investigations on the uniaxial tensile fatigue and bond behavior of CRC [3, 4].

To make CRC marketable in Germany, a huge research project 'C³ - Carbon Concrete Composite' was launched. The research project is divided into various subprojects. The subprojects 'C³ V1.2 – Standardization and Approval' as well as 'C³ V2.1 – Long-term Durability' deal with investigations regarding the static and cyclic long-term behavior of carbon reinforcements, which are partly summarized in [1-4, 28].

The main objective of the conducted fatigue investigations is the derivation of stress-cycle-curves, which are known from steel construction as S N curves (fatigue / Woehler curves). The German standard DIN 50100 'Load controlled fatigue testing - Execution and evaluation of cyclic tests at constant load amplitudes on metallic specimens and components' [29] serves as basis for testing and evaluation of the fatigue tests.

The cyclic load as a sinusoidal load-time-function is illustrated in Fig. 1. The terminology is based on [30].