

Australian/New Zealand Standard™

Structural steel welding

**Part 7: Welding of sheet steel
structures**



AS/NZS 1554.7:2014

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee WD-003, Welding of Structures. It was approved on behalf of the Council of Standards Australia on 24 September 2014 and on behalf of the Council of Standards New Zealand on 12 September 2014.
This Standard was published on 25 November 2014.

The following are represented on Committee WD-003:

Australasian Corrosion Association
Australian Chamber of Commerce and Industry
Australian Industry Group
Australian Steel Institute
Austroads
Bureau of Steel Manufacturers of Australia
Energy Networks Association
Engineers Australia
New Zealand Heavy Engineering Research Association
New Zealand Non-Destructive Testing Association
Steel Reinforcement Institute of Australia
University of Sydney
Welding Technology Institute of Australia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at www.saiglobal.com.au or Standards New Zealand web site at www.standards.co.nz and looking up the relevant Standard in the on-line catalogue.

For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of either Standards Australia or Standards New Zealand at the address shown on the back cover.

This Standard was issued in draft form for comment as DR AS/NZS 1554.7.

Australian/New Zealand Standard™

Structural steel welding

Part 7: Welding of sheet steel structures

Originated as AS/NZS 1554.7:2006.
Second edition 2014.
Reissued incorporating Amendment No. 1 (September 2015).

COPYRIGHT

© Standards Australia Limited/Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Australia) or the Copyright Act 1994 (New Zealand).

Jointly published by SAI Global Limited under licence from Standards Australia Limited, GPO Box 476, Sydney, NSW 2001 and by Standards New Zealand, Private Bag 2439, Wellington 6140.

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee WD-003, Welding of Structures, to supersede AS/NZS 1554.7:2006.

This Standard incorporates Amendment No. 1 (September 2015). The changes required by the Amendment are indicated in the text by a marginal bar and amendment number against the clause, note, table, figure or part thereof affected.

The objective of this Standard is to provide rules for the welding of a wide range of light gauge steel constructions designed in accordance with the requirements of AS/NZS 4600. Although this Standard has been specifically prepared for steel structures, it may be usefully applied to machine frames and other types of steel constructions.

Given the historical links between the requirements of AS/NZS 4600, *Cold-formed steel structures* and the American Welding Society's AWS D1.3, *Structural Welding Code—Sheet Steel*, this Standard takes cognizance of the requirements and practices associated with AWS D1.3, and the similar requirements contained within AS/NZS 1554.1, *Structural steel welding Part 1: Welding of steel structures*, for category GP quality welds.

This edition incorporates the following major changes to the 2006 edition:

(a) *Changes to the following Clauses:*

1.1, 1.7 (new title and text), 2.3.1, 2.3.3, 3.3.3, 4.1.2 [new Items (d), (f)-(j)], 4.2(b), 4.2(d) (correction), 4.3(e), 4.5.5.1, 4.5.5.3, 4.6.1.1, 4.6.1.2 (new Note), 4.7.1, 4.7.7, 4.8, 4.12.1, 4.12.2, 5.1, 5.2.4, 5.3.4, 6.1.2, 6.4 (Note 2), 6.5 (new Note), 7.2, 7.4, Appendix H (new), Bibliography (new).

(b) *Changes to the following Tables:*

4.6.1(A), 4.6.1(B), 4.6.1(C), 4.11(A), 4.11(B), 4.11(C) (new), 4.12.2(A), 4.12.2(B), 5.3.4(A), E1, E2.

(c) *Changes to the following Figures:*

3.2.5, 4.5.5.1 (Note 2 and title), 4.5.5.4 (title).

The Standard requires that weld preparations, welding consumables and welding procedures be qualified before commencement of welding. Prequalified joint preparations, welding consumables and welding procedures are also given in the Standard.

The Standard caters specifically for statically loaded structures and, similarly to AS/NZS 4600, does not consider brittle fracture requirements. Under circumstances where brittle fracture is considered likely, the user is instead referred to AS/NZS 1554.1. Whilst AS/NZS 4600 now caters for dynamic loading conditions, both AS/NZS 4600 and this Standard also refer the user to the more appropriate requirements of AS/NZS 1554.1 Category SP, or for high levels of dynamic loading (fatigue), to AS/NZS 1554.5, *Structural steel welding, Part 5: Welding of steel structures subject to high levels of fatigue loading*. This will ensure that appropriate levels of supervision and inspection will be applied to the relevant parts of the structure.

Statements expressed in mandatory terms in notes to tables and figures are deemed to be requirements of this Standard.

The terms 'normative' and 'informative' have been used in this Standard to define the application of the appendix to which they apply. A 'normative' appendix is an integral part of a Standard, whereas an 'informative' appendix is only for information and guidance.

CONTENTS

	<i>Page</i>
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE.....	5
1.2 EXCLUSIONS.....	6
1.3 INNOVATION	6
1.4 NORMATIVE REFERENCES	6
1.5 DEFINITIONS.....	6
1.6 SYMBOLS	7
1.7 MANAGEMENT OF QUALITY.....	7
1.8 SAFETY	7
SECTION 2 MATERIALS OF CONSTRUCTION	
2.1 PARENT MATERIAL.....	8
2.2 BACKING MATERIAL	8
2.3 WELDING CONSUMABLES.....	8
SECTION 3 DETAILS OF WELDED CONNECTIONS	
3.1 GENERAL.....	10
3.2 BUTT WELDS	10
3.3 FILLET WELDS	13
3.4 COMPOUND WELDS	14
3.5 SEAL WELDS.....	15
3.6 FLARE WELDS	15
3.7 ARC SPOT (PUDDLE) WELDS	16
3.8 ARC SEAM WELDS.....	18
3.9 ARC PLUG WELDS	19
SECTION 4 QUALIFICATION OF PROCEDURES AND PERSONNEL	
4.1 QUALIFICATION OF WELDING PROCEDURE.....	20
4.2 METHODS FOR QUALIFYING A WELDING PROCEDURE.....	22
4.3 PREQUALIFIED WELDING PROCEDURES.....	23
4.4 PORTABILITY OF QUALIFIED WELDING PROCEDURES	23
4.5 PREQUALIFIED JOINT PREPARATIONS	23
4.6 QUALIFICATION OF WELDING CONSUMABLES.....	31
4.7 QUALIFICATION OF WELDING PROCEDURE BY TESTING.....	38
4.8 EXTENSION OF QUALIFICATION	40
4.9 COMBINATION OF PROCESSES	41
4.10 RECORDS OF TESTS	41
4.11 REQUALIFICATION OF WELDING PROCEDURES	43
4.12 QUALIFICATION OF WELDING PERSONNEL	45

SECTION 5 WORKMANSHIP

5.1	PREPARATION OF EDGES FOR WELDING	51
5.2	ASSEMBLY	51
5.3	PREHEATING AND INTER-RUN CONTROL	53
5.4	WELDING UNDER ADVERSE WEATHER CONDITIONS	59
5.5	TACK WELDS	59
5.6	WELD DEPTH TO WIDTH RATIO	59
5.7	CONTROL OF DISTORTION AND RESIDUAL STRESS	60
5.8	BACKGOUGING AND REPAIR OF DEFECTS IN WELDS	60
5.9	TEMPORARY ATTACHMENTS	61
5.10	ARC STRIKES	61
5.11	CLEANING OF FINISHED WELDS	62
5.12	DRESSING OF BUTT WELDS	62

SECTION 6 QUALITY OF WELDS

6.1	METHODS OF INSPECTION AND PERMISSIBLE LEVELS OF IMPERFECTIONS	63
6.2	MAGNETIC PARTICLE EXAMINATION	67
6.3	LIQUID PENETRANT EXAMINATION	67
6.4	WELD DEFECTS	67
6.5	REPORTING	67

SECTION 7 INSPECTION

7.1	GENERAL	68
7.2	QUALIFICATIONS OF INSPECTORS	68
7.3	VISUAL INSPECTION OF WORK	68
7.4	NON-DESTRUCTIVE EXAMINATION OTHER THAN VISUAL	68

APPENDICES

A	NORMATIVE REFERENCED DOCUMENTS	70
B	BRITTLE FRACTURE	73
C	TYPICAL FORMS FOR WELDING PROCEDURES	76
D	MATTERS FOR RESOLUTION	79
E	WELDED JOINT AND PROCESS IDENTIFICATION	80
F	MIG BRAZING	86
G	BEND AND TORSION TESTS FOR SHEET STEELS	88
H	WELD PROCEDURE REQUIREMENTS ASSOCIATED WITH CHANGES TO THE WELDING CONSUMABLE CLASSIFICATION SYSTEM	94

BIBLIOGRAPHY	98
--------------------	----

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

Australian/New Zealand Standard
Structural steel welding

Part 7: Welding of sheet steel structures

SECTION 1 SCOPE AND GENERAL**1.1 SCOPE**

This Standard specifies requirements for the arc welding of steel structures made up of combinations of steel plate, sheet or sections, including pipe, hollow sections and built up sections (collectively referred to herein as sheet steels) up to 4.8 mm in thickness by the following processes:

- (a) Manual metal arc welding (MMAW).
- (b) Gas metal arc welding (GMAW or MIG), including pulsed mode.
- (c) Gas tungsten-arc welding (GTAW or TIG).
- (d) Flux-cored arc welding (FCAW).

The Standard is limited to the welding of steel parent material with a specified minimum yield strength not exceeding 550 MPa.

The Standard applies to the welding of steelwork in structures complying with AS/NZS 4600. The following limitations apply:

- (i) For other than fatigue conditions, where welded joints are governed by dynamic loading conditions, AS/NZS 1554.1 category SP applies.
- (ii) For welded joints subject to fatigue conditions (i.e. weld categories higher than detail category 118 of AS/NZS 4600), AS/NZS 1554.5 category FP.

Consistent with AS/NZS 4600, brittle fracture provisions have not been included in this Standard. For service temperatures colder than -10°C , the brittle fracture provisions of AS/NZS 1554.1 for materials and welding consumables apply (see Appendix B).

In addition to the abovementioned structures, the Standard applies to the welding of steelwork in applications other than structural.

The Standard specifies requirements equivalent to AS/NZS 1554.1 category GP arc welding. For the welding of sheet steels thicker than 4.8 mm, the requirements of AS/NZS 1554.1 apply.

For stud welding through the flat portion of decking or roofing onto supporting structural members, AS/NZS 1554.2 applies.

NOTES:

- 1 Further information on this Standard is given in WTIA Technical Note 11.
- 2 GMAW includes waveform controlled welding such as 'synergic', 'programmable', and 'microprocessor controlled' processes' e.g. pulsed spray transfer, controlled short circuit transfer.

1.2 EXCLUSIONS

The Standard does not apply to the welding of structures by the following processes:

- (a) Oxyacetylene welding (OAW).
- (b) Friction welding (FW).
- (c) Thermit welding (TW).
- (d) Resistance welding (RW).
- (e) Electroslag (including consumable guide) welding (ESW).
- (f) Electrogas welding (EGW).

NOTE: Resistance welds in structures complying with AS/NZS 4600 should be made in accordance with AWS C1.1 or AWS C1.3, as appropriate.

The Standard does not apply to the welding of pressure vessels and pressure piping.

The Standard does not cover the design of welded connections or permissible stresses in welds, nor the production, rectification or repair of castings.

1.3 INNOVATION

Any alternative materials, welding processes, consumables, methods of construction or testing that give equivalent results to those specified, but do not comply with the specific requirements of this Standard or are not mentioned in it, are not necessarily prohibited.

1.4 NORMATIVE REFERENCES

The normative documents referenced in this Standard are listed in Appendix A.

NOTE: Documents referenced for informative purposes are listed in the Bibliography.

1.5 DEFINITIONS

For the purpose of this Standard, the definitions given in AS 2812 and those below apply.

1.5.1 Fabricator

The person or organization responsible for the welding of the structure during fabrication or erection.

1.5.2 Inspecting authority

The authority having statutory powers to control the design and erection of buildings or structures.

NOTE: Where the structure is not subject to statutory jurisdiction, the principal is deemed to be the inspecting authority.

1.5.3 Inspector

A person employed by or acceptable to the inspecting authority or the principal for the purpose of inspecting welding in accordance with this Standard.

1.5.4 May

Indicates the existence of an option.

1.5.5 Principal

The purchaser or owner of the structure being fabricated or erected, or a nominated representative.

NOTE: The nominated representative should be suitably qualified to deal with the technical issues of this Standard.

1.5.6 Shall

Indicates that a statement is mandatory.

1.5.7 Should

Indicates a recommendation.

1.6 SYMBOLS

For the purpose of this Standard the symbols given in AS 1101.3 apply.

1.7 MANAGEMENT OF QUALITY

1.7.1 Quality management

Fabricators shall ensure that all welding and related activities prescribed within Clause 1.7.2 and this Standard are managed under a suitable quality management system.

Such a system should generally comply with the requirements of AS/NZS ISO 3834 and its parts, particularly where fabrication activities require the approval of the principal or inspecting authority, or where the fabrication of large, complex or critical structures is being undertaken.

1.7.2 Basic welding requirements

The basis of this Standard is that a weld shall—

- (a) be made in accordance with a qualified welding procedure;
- (b) be carried out by a welder suitably qualified to carry out such a procedure;
- (c) be carried out under the supervision of a welding supervisor who is employed by or contracted to the fabricator; and
- (d) comply with the appropriate requirements of this Standard.

For certain conditions prescribed herein, the welding procedure is deemed to be prequalified and may not require full qualification testing (see Clause 4.3 and Table 4.7.1).

NOTE: Fabricators may find it useful to refer to AS/NZS ISO 3834 and its parts where fabrication activities require the approval of the principal or the inspecting authority, or where the fabrication of large, complex or critical structures is being undertaken.

1.8 SAFETY

1.8.1 Safety equipment and procedures

Welding shall be carried out in accordance with the relevant requirements of AS 1470, AS 1674.1, AS 1674.2, AS 2865, AS/NZS 1336, AS/NZS 1337 and AS/NZS 1338.1.

1.8.2 Welding equipment

Welding plant and equipment shall comply with the relevant sections of appropriate regulations, and AS 2799, AS/NZS 1995, and AS 60974.1.

1.8.3 Other hazards

The fabricator shall identify and manage any other risks and hazards from welding that are not covered by Clauses 1.8.1 and 1.8.2. In particular, due consideration shall be given to the control and dispersal of emitted fumes, especially when welding through paints, primers and other surface coatings.

NOTES:

- 1 Guidance on the management of risk is given in AS/NZS ISO 31000.
- 2 Further guidance on safety precautions is given in WTIA Technical Notes 7 and 22.

SECTION 2 MATERIALS OF CONSTRUCTION

2.1 PARENT MATERIAL

The parent material to be welded shall—

- (a) be of a grade with a specified minimum yield strength not exceeding 550 MPa; and
- (b) comply with AS/NZS 1163, AS 1397, AS 1450, AS 1548, AS/NZS 1594, AS/NZS 1595, AS/NZS 3678, AS/NZS 3679.1, AS/NZS 3679.2, and NZS 3415, as appropriate.

NOTE: Any steel type from any Standard above may be welded to any other steel type from any Standard above, provided the requirements of this Standard are met for each of the steels.

With the exception of quenched and tempered steels, parent materials not identified to a Standard nominated in Item (b) above may be used provided one of the following requirements are met:

- (i) Testing of the material to determine compliance with any of the grade types in the Standards nominated in Item (b) above has been carried out to the satisfaction of the principal.
- (ii) A comparison of supplied test certificates with the requirements of any of the grade types in the Standards nominated in Item (b) above has been performed to the satisfaction of the principal.

NOTES:

- 1 For high-strength quenched and tempered steels, see AS/NZS 1554.4.
- 2 Steels relying on a strength increase from cold work may incur a loss of strength in the heat-affected zone of the weld.
- 3 For steels subject to design service temperatures colder than -10°C , refer to the brittle fracture provisions of AS/NZS 1554.1. Impact tests (not normally a requirement of this Standard) in addition to those prescribed by the Standards in Item (b) above may be required to establish compliance with AS/NZS 1554.1.

A1 | **‘Text deleted’**

2.2 BACKING MATERIAL

The weldability of permanently attached steel backing material shall be not less than that of the parent material.

Temporary backing material of any type may be used for welds, provided the finished weld complies with the requirements of this Standard.

2.3 WELDING CONSUMABLES

2.3.1 Electrodes and filler wires

Electrodes for manual metal arc welding shall comply with AS/NZS 4855 or AS/NZS 4857, as applicable (see Clause 4.6.1).

Electrodes or filler wires for processes other than manual metal arc welding shall comply with AS/NZS 1167.2, AS/NZS 14341, AS/NZS ISO 17632 or ISO 636, as applicable (see Clause 4.6.1).

Electrodes that do not comply with the above Standards may be used, provided that they are qualified in accordance with the requirements of Clause 4.6.2.