



Designation: D2170/D2170M – 18



Designation: 319/84 (89)

Standard Test Method for Kinematic Viscosity of Asphalts¹

This standard is issued under the fixed designation D2170/D2170M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers procedures for the determination of kinematic viscosity of liquid asphalts, road oils, and distillation residues of liquid asphalts all at 60 °C [140 °F] and of liquid asphalt binders at 135 °C [275 °F] (see table note, **11.1**) in the range from 6 to 100 000 mm²/s [cSt].

1.2 Results of this test method can be used to calculate viscosity when the density of the test material at the test temperature is known or can be determined. See **Annex A1** for the method of calculation.

NOTE 1—This test method is suitable for use at other temperatures and at lower kinematic viscosities, but the precision is based on determinations on liquid asphalts and road oils at 60 °C [140 °F] and on asphalt binders at 135 °C [275 °F] only in the viscosity range from 30 to 6000 mm²/s [cSt].

NOTE 2—Modified asphalt binders or asphalt binders that have been conditioned or recovered are typically non-Newtonian under the conditions of this test. The viscosity determined from this method is under the assumption that asphalt binders behave as Newtonian fluids under the conditions of this test. When the flow is non-Newtonian in a capillary tube, the shear rate determined by this method may be invalid. The presence of non-Newtonian behavior for the test conditions can be verified by measuring the viscosity with viscometers having different-sized capillary tubes. The defined precision limits in **11.1** may not be applicable to non-Newtonian asphalt binders.

1.3 **Warning**—Mercury has been designated by the United States Environmental Protection Agency (EPA) and many state agencies as a hazardous material that can cause central nervous system, kidney, and liver damage. Mercury, or its vapor, may be hazardous to health and corrosive to materials. Caution should be taken when handling mercury and mercury-containing products. See the applicable product Material Safety Data Sheet (MSDS) or Safety Data Sheet (SDS) for details and the EPA's website—<http://www.epa.gov/mercury/faq.htm>—for additional information. Users should be aware

that selling mercury, mercury-containing products, or both, in your state may be prohibited by state law.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.5 The text of this standard references notes and footnotes that provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- C670** Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials
- D8** Terminology Relating to Materials for Roads and Pavements
- D92** Test Method for Flash and Fire Points by Cleveland Open Cup Tester
- D341** Practice for Viscosity-Temperature Charts for Liquid Petroleum Products
- D445** Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (and Calculation of Dynamic Viscosity)

¹ This test method is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.44 on Rheological Tests. In the IP this test method is under the jurisdiction of the Standardization Committee.

Current edition approved Dec. 15, 2018. Published January 2019. Originally approved in 1963. Last previous edition approved in 2010 as D2170/D2170M – 10. DOI: 10.1520/D2170_D2170M-18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



[D446](#) Specifications and Operating Instructions for Glass Capillary Kinematic Viscometers
[D2162](#) Practice for Basic Calibration of Master Viscometers and Viscosity Oil Standards
[D2493/D2493M](#) Practice for Viscosity-Temperature Chart for Asphalt Binders
[D3666](#) Specification for Minimum Requirements for Agencies Testing and Inspecting Road and Paving Materials
[E1](#) Specification for ASTM Liquid-in-Glass Thermometers
[E77](#) Test Method for Inspection and Verification of Thermometers
[E879](#) Specification for Thermistor Sensors for General Purpose and Laboratory Temperature Measurements
[E1137/E1137M](#) Specification for Industrial Platinum Resistance Thermometers

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *density, n* —the mass per unit volume of liquid. The SI unit of density is 1 kg/m³. The cgs unit of density is 1 g/cm³.

3.1.2 *kinematic viscosity, n* —the ratio of the viscosity to the density of a liquid, measured as the resistance to flow of a liquid under gravity.

3.1.2.1 *Discussion*—The SI unit of kinematic viscosity is m²/s; for practical use, a submultiple (mm²/s) is more convenient. The cgs unit of kinematic viscosity is 1 cm²/s and is called a stoke (symbol St). The centistoke (1 cSt = 10⁻² St) is 1 mm²/s and is often used.

3.1.3 *Newtonian viscosity, n* —the viscosity of a liquid that is shear-rate independent in which the rate of shear is linearly proportional to the shearing stress.

3.1.4 *non-Newtonian viscosity, n* —the viscosity of a liquid that is shear-rate dependent in which the rate of shear is not linearly proportional to the shearing stress.

3.1.5 *road oil, n* —a slow-curing, petroleum-derived liquid used to control dust or act as a waterproofing sealant.

3.1.6 *viscosity (coefficient of), n* —the ratio between the applied shear stress and rate of shear is called the coefficient of viscosity.

3.1.6.1 *Discussion*—This coefficient is a measure of the resistance to flow of a liquid. It is commonly called the viscosity of the liquid. The cgs unit of viscosity is 1 g/cm·s (1 dyne·s/cm²) and is called a poise (P). The SI unit of viscosity is 1 Pa·s (1 N·s/m²) and is called a Pascal-second. One Pa·s is equivalent to 10 P.

3.2 For definitions of other terms used in this standard, refer to Terminology [D8](#).

4. Summary of Test Method

4.1 The time is measured for a fixed volume of the liquid to flow through the capillary of a calibrated glass capillary viscometer under an accurately reproducible head and at a closely controlled temperature. The kinematic viscosity is then calculated by multiplying the efflux time in seconds by the viscometer calibration factor.

5. Significance and Use

5.1 The kinematic viscosity characterizes flow behavior. The method is used to determine the consistency of liquid asphalt as one element in establishing the uniformity of shipments or sources of supply. The specifications are usually at temperatures of 60 and 135 °C.

NOTE 3—The quality of the results produced by this standard are dependent on the competence of the personnel performing the procedure and the capability, calibration, and maintenance of the equipment used. Agencies that meet the criteria of Specification [D3666](#) are generally considered capable of competent and objective testing, sampling, inspection, etc. Users of this standard are cautioned that compliance with Specification [D3666](#) alone does not completely ensure reliable results. Reliable results depend on many factors; following the suggestions of Specification [D3666](#) or some similar acceptable guideline provides a means of evaluating and controlling some of those factors.

6. Apparatus

6.1 *Viscometers*, capillary-type, made of borosilicate glass, annealed, suitable for this test are described in [Annex A2](#) and include the following:

6.1.1 Cannon-Fenske viscometer for opaque liquids.

6.1.2 Zeitfuchs Cross-Arm viscometer.

6.1.3 Lantz-Zeitfuchs viscometer.

6.1.4 BS U-Tube modified reverse-flow viscometer.

6.1.5 Calibrated viscometers are available from commercial suppliers. Details regarding calibration of viscometers are given in [Annex A3](#).

6.2 *Thermometers*—Calibrated thermometers with suitable range and estimated measurement uncertainty of 0.02 °C [0.04 °F] or less at 95 % confidence interval listed on the calibration certificate and is one of the following:

6.2.1 A liquid-in-glass thermometer that is calibrated annually. The calibration shall be verified at the ice point in accordance with [Appendix X1](#). ASTM Kinematic Viscosity Thermometers 47C and 47F conforming to Specification [E1](#), and IP 35C and 35F are suitable for use at 60 °C [140 °F], and ASTM Kinematic Viscosity Thermometers 110C and 110F are suitable for use at 135 °C [275 °F].

NOTE 4—The specified thermometers in [6.2.1](#) are standardized as “total immersion” thermometers, which are designed to indicate temperatures correctly when just that portion of the thermometer containing the liquid is exposed to the temperature being measured and the remainder of the stem and expansion chamber at the top of the thermometer exposed to the room temperature. The practice of completely submerging the thermometer is not recommended. When a “total immersion” thermometer is completely submerged, corrections for each individual thermometer based on calibration under conditions of complete submergence must be determined and applied. If the thermometer is completely submerged in the bath during use, the pressure of the gas in the expansion chamber will be higher or lower than during standardization, and may cause high or low readings on the thermometer.

6.2.2 A platinum resistance thermometer (PRT) with a sensor which conforms to the requirements of Specification [E1137/E1137M](#). The thermometer shall be calibrated annually as a single unit and have a three- or four-wire connection configuration. The sensing element shall be immersed to the depth specified by the manufacturer adjacent to the capillary tube.

NOTE 5—A minimum of 50 mm (2 in.) of the thermometer sheath



(wire-connecting side) shall not be subjected to the bath medium unless otherwise specified by the manufacturer.

6.2.3 A thermistor thermometer with sensor, which conforms to the requirements of Specification E879, calibrated annually as a single unit. The sensing element of the thermistor shall be completely immersed in the bath adjacent to the capillary tube.

NOTE 6—The use of the thermometric devices specified in 6.2.2 and 6.2.3 are understood to introduce bias in the precision in this method.

6.3 *Bath*—A bath suitable for immersion of the viscometer so that the liquid reservoir or the top of the capillary, whichever is uppermost, is at least 20 mm below the upper bath level, and with provisions for visibility of the viscometer and the thermometer. Firm supports for the viscometer shall be provided, or the viscometer may be an integral part of the bath. The efficiency of the stirring and the balance between heat losses and heat input must be such that the temperature of the bath medium does not vary by more than ± 0.03 °C [± 0.05 °F] over the length of the viscometer, or from viscometer to viscometer in the various bath positions at 60 °C [140 °F].

NOTE 7—Distilled water is a suitable bath liquid for determinations at 60 °C [140 °F]. USP White Oil with a flash point above 215 °C [420 °F] has been found suitable for determinations at 135 °C [275 °F]. The flash point is determined in accordance with Test Method D92.

6.4 *Timer*—A stopwatch or other timing device, graduated in divisions of 0.1 s or less and accurate to within 0.05 % when tested over intervals of not less than 15 min. Timing devices for this test method must be standardized at least every twelve months.

6.4.1 *Electrical Timing Devices* may be used only on electrical circuits, the frequencies of which are controlled to an accuracy of 0.05 % or better.

6.4.1.1 Alternating currents, the frequencies of which are intermittently and not continuously controlled, as provided by some public power systems, can cause large errors, particularly over short timing intervals, when used to actuate electrical timing devices.

7. Preparation of Sample

7.1 To minimize loss of volatile constituents and to obtain reproducible results, proceed as follows:

7.1.1 *Procedure for Liquid Asphalts, Distillation Residues, and Road Oil:*

7.1.1.1 Allow sealed samples, as received, to reach room temperature.

7.1.1.2 Open the sample container and mix the sample thoroughly by stirring for 30 s, taking care to avoid the entrapment of air. If the sample is too viscous for such stirring, place the sample in the tightly sealed container in a bath or oven maintained at 63 ± 3 °C [145 ± 5 °F] until it becomes sufficiently liquid for stirring.

7.1.1.3 Immediately charge the viscometer, or, if the test is to be made at a later time, pour approximately 20 mL into one or more clean, dry containers having a capacity of approximately 30 mL and immediately seal with an airtight closure.

7.1.1.4 For materials with kinematic viscosities at 60 °C [140 °F] above 800 mm²/s [cSt], heat the 20-mL sample in the sealed container in an oven or bath maintained at 63 ± 3 °C

[145 ± 5 °F] until it is sufficiently liquid for a convenient transfer into the viscometer. Such heating should not exceed 30 min.

7.1.2 *Procedure for Liquid Asphalts and Distillation Residues in the Range from 6 to 100 000 mm²/s [cSt]:*

7.1.2.1 Heat the sample with care to prevent local overheating until it has become sufficiently fluid to pour, occasionally stirring the sample to aid heat transfer and to ensure uniformity.

7.1.2.2 Transfer a minimum of 20 mL into a suitable container and heat to 135 ± 5.5 °C [275 ± 10 °F], stirring occasionally to prevent local overheating and taking care to avoid the entrapment of air.

8. Procedure

8.1 The specific details of operation vary somewhat for the various types of viscometers. See the detailed descriptions of viscometers in Annex A2 for instructions for using the type of viscometer selected. In all cases, however, follow the general procedure described in 8.2 – 8.8.

8.2 Maintain the bath at the test temperature within ± 0.01 °C [± 0.02 °F]. Apply the necessary corrections, if any, to all thermometer readings.

8.3 Select a clean, dry viscometer which will give an efflux time greater than 60 s and preheat to test temperature.

8.4 Charge the viscometer in the manner dictated by the design of the instrument, as prescribed in Annex A2.

8.5 Allow the charged viscometer to remain in the bath long enough to reach the test temperature, as prescribed in Annex A2.

8.6 Start the flow of asphalt in the viscometer as prescribed in Annex A2.

8.7 Measure to within 0.1 s the time required for the leading edge of the meniscus to pass from the first timing mark to the second. If this efflux time is less than 60 s, select a viscometer of smaller capillary diameter and repeat the operation.

8.8 Upon completion of the test, clean the viscometer thoroughly by several rinsings with an appropriate solvent completely miscible with the sample, followed by a completely volatile solvent. Dry the tube by passing a slow stream of filtered dried air through the capillary for 2 min, or until the last trace of solvent is removed. Alternatively, the viscometer may be cleaned in a glass cleaning oven at a temperature not to exceed 500 °C [932 °F], followed by rinses with distilled or deionized water, residue-free acetone, and filtered dry air. Periodically, if deposits are observed, clean the instrument with a strong acid cleaning solution to remove organic deposits, rinse thoroughly with distilled water and residue-free acetone, and dry with filtered dry air.

NOTE 8—The cleaning oven may burn off the glue that connects the viscometer tube to the holder.

8.8.1 Chromic acid cleaning solution may be prepared by adding, with the usual precautions, 800 mL of concentrated sulphuric acid to a solution of 92 g of sodium dichromate in 458 mL of water. The use of similar commercially available