PD 6691:2015+A1:2016



**BSI Standards Publication** 

# **PUBLISHED DOCUMENT**

Guidance on the use of BS EN 13108, Bituminous mixtures – Material specifications

This publication is not to be regarded as a British Standard



### Publishing and copyright information

The BSI copyright notice displayed in this document indicates when the document was last issued.

© The British Standards Institution 2016 Published by BSI Standards Limited 2016

ISBN 978 0 580 95869 4

ICS 93.080.20

The following BSI references relate to the work on this document: Committee reference B/510 Draft for comment 14/30283621 DC

### **Publication history**

First published, June 2007 Second edition, December 2010 Third (present) edition, March 2015

#### Amendments issued since publication

Date	Text affected
December 2016	A1 – See Foreword

# Contents

Foreword iii

- 0 Introduction 1
- **1** Scope *2*
- 2 Normative references 2
- 3 Terms, definitions and abbreviations 3
- 4 Constituent materials 5
- 5 Mixture composition 7
- **6** BS EN 13108-1 asphalt concrete specification requirements *9*
- 7 BS EN 13108-2 asphalt concrete for very thin layers specification requirements 15
- 8 BS EN 13108-3 soft asphalt specification requirements 16
- **9** BS EN 13108-4 hot rolled asphalt specification requirements *16*
- 10 BS EN 13108-5 stone mastic asphalt specification requirements 20
- 11 BS EN 13108-6 mastic asphalt 24
- 12 BS EN 13108-7 porous asphalt 24
- 13 BS EN 13108-8 reclaimed asphalt specification requirements 25
- 14 Assessment and verification of constancy of performance 25

### Annexes

Annex A BS EN 13108 mixture specifications 40

Annex B BS EN 13108-1 asphalt concrete – example specification 40 Annex C BS EN 13108-4 hot rolled asphalt – example specification 61 Annex D BS EN 13108-5 stone mastic asphalt – example specification 73

Bibliography 79

## List of figures

Figure B.1 – Example specification giving the UK choice for specifying asphalt concrete in accordance with BS EN 13108-1 40

Figure C.1 – Example specification giving the UK choice for specifying HRA in accordance with BS EN 13108-4 61

Figure D.1 – Example specification giving the UK choice for specifying SMA in accordance with BS EN 13108-5 73

# List of tables

Table 1 – References to protocols in BS 594987:2015 27 Table 2 – Type-testing sample preparation and testing requirements for UK asphalt concrete mixtures conforming to BS EN 13108-1 28 Table 3 – Type-testing sample preparation and testing requirements for UK HRA mixtures conforming to BS EN 13108-4 29 Table 4 – Type- testing sample preparation and testing requirements for UK SMA mixtures conforming to BS EN 13108-5 30 Table 5 – Permitted mean deviations from target (extracted from BS EN 13108-21:2016, Table A.1) 34 Table 6 – Determination of operating compliance level of plant for single results (extracted from BS EN 13108-21:2016, Table A.3) 34 Table 7 – Minimum frequency for analysis of finished product (tonnes/test) (extracted from BS EN 13108-21:2016, Table A.4) 35 Table 8 – Tolerances to be applied to the declared target grading and binder content (extracted from BS EN 13108-21:2016, Table A.1) 36 Table 9 – Example of a declared specification AC 32 HDM base 40/60 rec 37 Table 10 – Example of a declared specification AC 6 dense surf 160/220 PSV 60 38 Table 11 – Example of a declared specification HRA 35/14F surf 40/60 des 39 Table 12 – Next harder grades for recovered binder assessment 39 Table A.1 – Importance of mixture specifications 40

Table B.1 – Aggregate grading target limits for 32 mm designed dense/HDM/HMBbase mixtures (AC 32 dense/HDM/HMB base XX/YY des)46

Table B.2 – Binder grades for design base and binder course mixtures46

Table B.3 – Minimum target binder content for designed dense base mixtures46 Table B.4 – Limiting wheel tracking requirements for site classifications 47 Table B.5 – Aggregate grading target limits for 32 mm designed dense/HDM/HMB binder course mixtures (AC 32 dense/HDM/HMB bin XX/YY des) 48 Table B.6 – Aggregate grading target limits for 20 mm designed dense/HDM/HMB binder course mixtures (AC 20 dense/HDM/HMB bin XX/YY des) 48 Table B.7 – Minimum target binder content for designed binder course mixtures 49 Table B.8 – Aggregate grading target limits for 20 mm, 14 mm and 10 mm EME2 mixtures (AC 20/14/10 EME2 base/bin XX/YY des) 50 Table B.9 – Minimum target binder content,  $B_{act}$  50 Table B.10 – Number of gyrations 50 Table B.11 – Target limits for composition for recipe dense base and binder course mixtures (AC D dense/HDM base/bin XX/YY rec) 52 Table B.12 – Target limits for composition for open graded binder course mixtures [AC D open bin XX/YY (grav)] 53 Table B.13 – Target limits for composition for open graded surface course mixtures (AC 14 or 10 open surf XX/YY) 54 Table B.14 – Target limits for composition for close graded surface course mixtures (AC 14 or 10 close surf XX/YY) 55 Table B.15 – Target limits for composition for dense, medium graded and fine graded surface course mixtures (AC D dense/med/fine surf XX/YY) 56 Table B.16 – Guidance on selection of binder grades 57 Table B.17 – Maximum temperature of the mixture 57 Table B.18 – Aggregate grading target limits for 14 mm and 10 mm BBA mixtures (AC 14 or 10 BBA C bin XX/YY des) 58 Table B.19 – Aggregate grading target limits for 14 mm and 10 mm BBA mixtures (AC 14 or 10 BBA C/D surf XX/YY des) 58 Table B.20 – Minimum target binder content, Bact 58 Table B.21 – Number of gyrations and percentage of air voids 59 Table B.22 – Proportional rut depth, P, at 60 °C and 10000 cycles 59 Table B.23 – Stiffness modulus at 15 °C 60 Table B.24 – Acceptable strain in fatigue 60 Table B.25 – Maximum temperature of the mixture 61 Table C.1 – Limits for target composition for base and binder course mixtures 64 Table C.2A – Limits for target composition for surface course mixtures, Type F mixtures – Design and recipe target aggregate gradings (HRA %/D F surf XX/YY des/rec) 66 Table C.2B – Limits for target composition for surface course mixtures, Type F recipe mixtures - target binder content (HRA %/D F surf XX/YY rec) 67 Table C.2C – Limits for target composition for surface course mixtures, Type C mixtures – Design target aggregate gradings (HRA %/D C surf XX/YY des) 68 Table C.3 – Limiting wheel tracking requirements for site classifications 70 Table C.4 – Maximum temperature of the mixture 70 Table C.5 – Compliance grading of chippings 72 Table D.1 – Limits for target composition for SMA mixtures 76 Table D.2 – Limiting wheel tracking recommendations for site classifications 77 Table D.3 – Maximum temperature of the mixture 78

Summary of pages

This document comprises a front cover, an inside front cover, pages i to iv, pages 1 to 80, an inside back cover and a back cover.

# Foreword

# **Publishing information**

This Published Document is published by BSI Standards Limited, under licence from The British Standards Institution, and came into effect on 31 March 2015. It was prepared by Subcommittee B/510/1, *Asphalt products* and under the authority of Technical Committee B/510, *Road materials*. A list of organizations represented on this committee can be obtained on request to its secretary.

## Supersession

PD 6691:2015+A1:2016 supersedes PD 6691:2015, which is withdrawn.

Text introduced or altered by Amendment No. 1 is indicated in the text by tags A Minor editorial changes are not tagged.

## **Relationship with other publications**

This Published Document gives non-contradictory, complimentary information for use in the UK with BS EN 13108.

## Use of this document

This publication is not to be regarded as a British Standard.

As a guide, this Published Document takes the form of guidance and recommendations. It should not be quoted as if it were a specification and particular care should be taken to ensure that claims of compliance are not misleading.

Any user claiming compliance with this Published Document is expected to be able to justify any course of action that deviates from its recommendations.

### **Presentational conventions**

The guidance in this Published Document is presented in roman (i.e. upright) type. Any recommendations are expressed in sentences in which the principal auxiliary verb is "should".

The word "may" is used in the text to express permissibility, e.g. as an alternative to the primary recommendation of the Clause. The word "can" is used to express possibility, e.g. a consequence of an action or an event.

Commentary, explanation and general informative material is presented in smaller italic type, and does not constitute a normative element.

### **Contractual and legal considerations**

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a Published Document cannot confer immunity from legal obligations.

# PUBLISHED DOCUMENT

# 0 Introduction

# 0.1 Overview of BS EN 13108

BS EN 13108 is based on a common format and common principles. The overall principle is to provide a way for the target composition of a mixture to be declared in a standard way and demonstrate that, at that target composition, it has certain defined properties. Each mixture formulation needs a declaration of the properties which are being claimed, demonstrated through a product-type testing procedure. In the simplest case it can be just grading and binder content. In more complex situations it can include performance-related properties, such as stiffness, deformation resistance and fatigue resistance. The demonstration of performance and conformity of the mixture on an ongoing basis requires the producer to undertake factory production control. This is a quality management procedure involving defined inspection and test regimes, and conformity criteria to prove that the mixture conforms to the declared target composition within defined tolerances.

BS EN 13108 offers a degree of choice in many aspects, such as ways of describing composition, types of constituents, properties, and means of specimen preparation for product-type testing. In many cases, this choice is indicated by the words "should be as specified". For BS EN 13108 to be practicably workable in the UK there needs to be standardization from amongst these choices so that producers know what to declare through product-type testing and purchasers know what to ask for. This Published Document gives the recommended choices for the mixtures most commonly used in the UK.

BS EN 13108 contains requirements only for the loose mixture, i.e. "in the back of the truck". The requirements for the laying of asphalts are retained in BS 594987, and conformity to BS 594987 is essential to ensure the durability of the finished work.

For recipe mixtures BS EN 13108 adopts the principle of a declared target composition selected from a permitted range which is different from the fixed composition envelope format of previous British Standards (which specified asphalt mixtures). This UK guidance gives recommendations for an approach to using BS EN 13108 to arrive at mixtures similar to those which have been traditionally used over many years. These are included as example specifications in Annex B, Annex C and Annex D of this Published Document.

BS EN 13108 includes provisions for the use of reclaimed asphalt in asphalt mixtures. BS EN 13108-8 provides a means of defining and classifying the properties of reclaimed asphalt. This Published Document gives guidance on a means of regulating the use of reclaimed asphalt.

# 0.2 Assessment and verification of constancy of performance

From 1 July 2013 the Construction Products Regulation 2013 [1] was fully implemented across all EU member states. It is a requirement of BS EN 13108 product standards that an asphalt product supplied in conformity with one of the parts of BS EN 13108 is assessed for product type and for conformity utilizing Part 20 and Part 21. This process is called assessment and verification of constancy of performance (AVCP). The end result of the AVCP process is the CE marking of the product confirming that it meets the performance requirements as detailed in the declaration of performance.

BS EN 13108-20 identifies the way in which the performance of a mixture composition to the requirements of the product standards is to be determined.

BS EN 13108-21 specifies procedures to be adopted during production to ensure product constancy and conformity with declared performance.

BS EN 13108-20 calls up test methods from the BS EN 12697 series of asphalt testing standards. Separate guidance on these test methods is given in PD 6692.

# 0.3 Mathematical nomenclature

To accord with European nomenclature protocols, the nature of mathematical notation adopted in this Published Document is that employed in the European Standard.

When denoting a decimal fraction, European notation employs a comma (,). For example, the "six point three" millimetre sieve (6.3 mm) is denoted as 6,3 mm.

# 1 Scope

This Published Document gives guidance on the use of BS EN 13108-1:2006, BS EN 13108-2:2008, BS EN 13108-4:2006, BS EN 13108-5:2006, BS EN 13108-7:2006, BS EN 13108-8:2005, BS EN 13108-20:2006 and A BS EN 13108-21:2016 A.

Clause **1** to Clause **10** of this Published Document give general guidance and background information on BS EN 13108.

Annex A gives guidance on the importance of BS EN 13108 mixture specifications. Annex B contains an example specification which gives the UK choice for specifying asphalt concrete in accordance with BS EN 13108-1. Annex C contains an example specification which gives the UK choice for specifying hot rolled asphalt in accordance with BS EN 13108-4. Annex D contains an example specification which gives the UK choice for specifying stone mastic asphalt in accordance with BS EN 13108-5.

This Published Document does not give guidance on BS EN 13108-6 as this standard is either rarely used in the UK or covered by other guidance.

This Published Document is applicable to mixtures for use on roads and other paved areas, including airfields. Detailed provisions for airfields are specified elsewhere.

NOTE 1 For airfield installations on the defence estate, guidance is given in the Defence Infrastructure Organisation Practitioner's Guide 06/11 [2].

NOTE 2 There are several asphalt mixtures in general use which have not been covered by British Standards but which are now covered in BS EN 13108. These are stone mastic asphalt, covered by BS EN 13108-5, and asphalt concrete for very thin layers (thin surfacing), covered by BS EN 13108-2.

# 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

# **Standards publications**

BS EN 1097-6, Tests for mechanical and physical properties of aggregates – Determination of particle density and water absorption

BS EN 1426 (BS 2000-49), Bitumen and bituminous binders – Determination of needle penetration

BS EN 12591, Bitumen and bituminous binders – Specifications for paving grade bitumens

BS EN 12697-3, Bituminous mixtures – Test methods for hot mix asphalt – Part 3: Bitumen recovery: Rotary evaporator

BS EN 12697-26, Bituminous mixtures – Test methods for hot mix asphalt – Part 26: Stiffness

BS EN 13043, Aggregates for bituminous mixtures and surface treatments for roads, airfields and other trafficked areas

BS EN 13108-1:2006, Bituminous mixtures – Material specifications – Part 1: Asphalt Concrete

BS EN 13108-4:2006, Bituminous mixtures – Material specifications – Part 4: Hot Rolled Asphalt

BS EN 13108-5:2006, Bituminous mixtures – Material specifications – Part 5: Stone Mastic Asphalt

BS EN 13108-7, Bituminous mixtures – Material specifications – Part 7: Porous Asphalt

BS EN 13108-8, Bituminous mixtures – Material specifications – Part 8: Reclaimed asphalt

BS EN 13108-20:2006, Bituminous mixtures – Material specifications – Part 20: Type testing

A) BS EN 13108-21:2016, Bituminous mixtures – Material specifications – Part 21: Factory Production Control (A)

BS EN 13924, Bitumen and bituminous binders – Specifications for hard paving grade bitumens

# **Other publications**

[N1] HIGHWAYS AGENCY. Manual of Contract Documents for Highway Works – Volume 1: Specification for Highway Works. 2015<sup>1)</sup>

# 3 Terms, definitions and abbreviations

# 3.1 Terms and definitions

For the purposes of this British Standard, the terms and definitions used in BS EN 13108, including the following, apply.

### 3.1.1 composition

### 3.1.1.1 mixture formulation

composition of a single mixture expressed as a target composition

NOTE 1 Two ways of declaring mixture composition are required because some countries traditionally work in terms of the theoretical percentages added in a laboratory mixture design, whereas others work in terms of the composition found on analysis.

NOTE 2 The protocol adopted in the UK is to always work in terms of composition found on analysis, i.e. output target composition.

### 3.1.1.2 output target composition

expression of a mixture formulation in terms of the constituent materials and the mid-point grading and soluble binder content to be found on analysis

NOTE This is usually the result of a production validation.

Available at: http://www.standardsforhighways.co.uk/mchw/vol1/index.htm [last viewed 24 March 2015]