

DIN EN 13381-8



ICS 13.220.50

Supersedes
DIN EN 13381-8:2010-09
Test methods for determining the contribution to the fire resistance of structural members –
Part 8: Applied reactive protection to steel members;
English version EN 13381-8:2013,
English translation of DIN EN 13381-8:2013-08

Prüfverfahren zur Bestimmung des Beitrages zum Feuerwiderstand von tragenden Bauteilen –

Teil 8: Reaktive Ummantelung von Stahlbauteilen;

Englische Fassung EN 13381-8:2013,

Englische Übersetzung von DIN EN 13381-8:2013-08

Méthodes d'essai pour déterminer la contribution à la résistance au feu des éléments de construction –

Partie 8: Protection réactive appliquée aux éléments en acier;

Version anglaise EN 13381-8:2013,

Traduction anglaise de DIN EN 13381-8:2013-08

Document comprises 78 pages

Translation by DIN-Sprachendienst.

In case of doubt, the German-language original shall be considered authoritative.



A comma is used as the decimal marker.

National foreword

This document (EN 13381-8:2013) has been prepared by Technical Committee CEN/TC 127 “Fire safety in buildings” (Secretariat: BSI, United Kingdom).

The responsible German body involved in its preparation was the *Normenausschuss Bauwesen* (Building and Civil Engineering Standards Committee), Working Committee NA 005-52-02 AA *Brandverhalten von Baustoffen und Bauteilen — Bauteile*.

Amendments

This standard differs from DIN EN 13381-8:2010-09 as follows:

- a) normative references have been updated;
- b) a change has been made to the test method to introduce measures allowing loaded beams to reach a deflection of $L/30$;
- c) in addition, the graphical assessment method now includes a point to point method of constructing lines and a new virtual data point related to furnace temperature.
- d) Annex G has been deleted;
- e) the figures have been editorially revised.

Previous editions

DIN V ENV 13381-4: 2003-09
DIN EN 13381-8: 2010-09

English Version

**Test methods for determining the contribution to the fire
resistance of structural members - Part 8: Applied reactive
protection to steel members**

Méthodes d'essai pour déterminer la contribution à la
résistance au feu des éléments de construction - Partie 8 :
Protection réactive appliquée aux éléments en acier

Prüfverfahren zur Bestimmung des Beitrages zum
Feuerwiderstand von tragenden Bauteilen - Teil 8: Reaktive
Ummantelung von Stahlbauteilen

This European Standard was approved by CEN on 10 February 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	4
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions, symbols and units.....	7
3.1 Terms and definitions.....	7
3.2 Symbols and units	9
4 Test equipment	11
4.1 General.....	11
4.2 Furnace.....	11
4.3 Loading equipment	11
5 Test conditions	11
5.1 General.....	11
5.2 Support and loading conditions.....	11
5.3 Loading.....	12
6 Test specimens	12
6.1 General.....	12
6.2 Size of test specimens.....	13
6.3 Construction of steel test specimens	14
6.4 Composition of steel sections.....	15
6.5 Properties of fire protection materials	15
6.6 Selection of test specimens	16
7 Installation of the test specimens	21
7.1 Loaded beam.....	21
7.2 Unloaded beams	22
7.3 Loaded columns	22
7.4 Unloaded columns.....	22
7.5 Test specimen installation patterns.....	22
7.6 Furnace load	23
8 Conditioning of the test specimens	23
9 Application of instrumentation.....	23
9.1 General.....	23
9.2 Instrumentation for measurement and control of furnace temperature	23
9.3 Instrumentation for measurement of steel temperatures.....	24
9.4 Instrumentation for the measurement of pressure.....	25
9.5 Instrumentation for the measurement of deformation	25
9.6 Instrumentation for the measurement of load	25
10 Test procedure	26
10.1 General.....	26
10.2 Furnace temperature and pressure.....	26
10.3 Application and control of load.....	26
10.4 Temperature of steelwork.....	26
10.5 Deflection	27
10.6 Observations.....	27
10.7 Termination of test.....	27
11 Test results.....	27
11.1 Acceptability of test results.....	27

11.2	Presentation of test results	28
12	Test report	29
13	Assessment	29
13.1	General	29
13.2	Temperature data	30
13.3	Correction for discrepancy in stickability and insulation performance over the thickness range tested	30
13.4	Assessment procedures for thermal performance	30
13.5	Acceptability of the assessment method used and the resulting analysis – criteria for acceptability	30
14	Report of the assessment	31
15	Limits of the applicability of the results of the assessment	32
Annex A	(normative) Test method to the smouldering fire (slow heating curve)	49
A.1	Introduction	49
A.2	Test equipment	49
A.3	Test specimens	49
A.4	Termination of test	50
A.5	Evaluation of the results	50
Annex B	(normative) Measurement of properties of fire protection materials	51
B.1	Introduction	51
B.2	Thickness of fire protection materials	51
B.3	Identification	52
Annex C	(normative) Fixing of thermocouples to steel work and routing of cables	53
C.1	Introduction	53
C.2	Types of thermocouples	53
C.3	Fixing of thermocouples	53
C.4	Routing of thermocouple wires	53
C.5	Connection of thermocouples	54
C.6	Thermocouple failures	54
Annex D	(normative) Correction of data/Nominal thickness	55
D.1	Correction of data	55
D.2	Nominal thickness - Graphical method	58
Annex E	(normative) Methods of assessment of fire protection system performance	59
E.1	General	59
E.2	Graphical Approach	59
E.3	Differential formula analysis (variable λ approach) methodology	65
E.4	Differential formula analysis (constant λ approach) methodology	70
E.5	Numerical regression analysis	71
Annex F	(normative) Tables of section sizes	74
Bibliography	76

Foreword

This document (EN 13381-8:2013) has been prepared by Technical Committee CEN/TC 127 “Fire safety in buildings”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2013, and conflicting national standards shall be withdrawn at the latest by November 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13381-8:2010.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

With respect to the previous version, the following changes have been made:

- A change has been made to the test method to introduce of a means allowing loaded beams to reach a deflection of $L/30$.
- In addition the graphical assessment method now includes a point to point method of constructing lines and a new virtual data point related to furnace temperature.

This document is compatible with EN 13381-4 and specifically deals with the testing and assessment of reactive coatings designed to protect structural steel.

This document is part of the EN 13381 series with the general title *Test methods for determining the contribution to the fire resistance of structural members*. Other parts of this series are:

- *Part 1: Horizontal protective membranes;*
- *Part 2: Vertical protective membranes;*
- *Part 3: Applied protection to concrete members;*
- *Part 4: Applied passive protection to steel members;*
- *Part 5: Applied protection to concrete/profiled sheet steel composite members;*
- *Part 6: Applied protection to concrete filled hollow steel columns;*
- *Part 7: Applied protection to timber members;*
- *Part 8: Applied reactive protection to steel members (the present document).*

Caution

The attention of all persons concerned with managing and carrying out this fire resistance test, is drawn to the fact that fire testing can be hazardous and that there is a possibility that toxic and/or harmful smoke and gases can be evolved during the test. Mechanical and

operational hazards can also arise during the construction of test elements or structures, their testing and the disposal of test residues. An assessment of all potential hazards and risks to health should be made and safety precautions should be identified and provided. Written safety instructions should be issued. Appropriate training should be given to relevant personnel. Laboratory personnel should ensure that they follow written safety instructions at all times. The specific health and safety instructions contained within this standard should be followed.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies a test method for determining the contribution made by applied reactive fire protection systems to the fire resistance of structural steel members, which can be used as beams or columns. It considers only sections without openings in the web. It is not directly applicable to structural tension members without further evaluation. Results from analysis of I or H - sections are directly applicable to angles, channels and T-sections for the same section factor, whether used as individual elements or as bracing. This standard does not apply to solid bar or rod.

It covers fire protection systems that involve only reactive materials and not to passive fire protection materials as defined in this document.

The evaluation is designed to cover a range of thicknesses of the applied fire protection material, a range of steel sections, characterised by their section factors, a range of design temperatures and a range of valid fire protection classification periods.

This European Standard contains the fire test procedures, which specifies the tests which should be carried out to determine the ability of the fire protection system to remain coherent and attached to the steelwork, and to provide data on the thermal characteristics of the fire protection system, when exposed to the standard temperature/time curve specified in EN 1363-1.

In special circumstances, where specified in National Building Regulations, there can be a need to subject reactive protection material to a smouldering curve; the test for this and the special circumstances for its use are described in Annex A.

The fire test methodology makes provision for the collection and presentation of data, which can be used as direct input to the calculation of fire resistance of steel structural members in accordance with the procedures given in EN 1993-1-2 and EN 1994-1-2.

This European Standard also contains the assessment, which prescribes how the analysis of the test data shall be made and gives guidance on the procedures by which interpolation should be undertaken.

The assessment procedure is used to establish:

- a) on the basis of temperature data derived from testing loaded and unloaded sections, a correction factor and any practical constraints on the use of the fire protection system under fire test conditions, (the physical performance);
- b) on the basis of the temperature data derived from testing short steel sections, the thermal properties of the fire protection system, (the thermal performance).

The limits of applicability of the results of the assessment arising from the fire test are defined, together with permitted direct application of the results, to different steel sections and grades and to the fire protection system.

The results of the test and assessment obtained according to this standard are directly applicable to steel sections of I and H cross sectional shape and hollow sections.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1363-1, *Fire resistance tests — Part 1: General requirements*