

## DIN EN 13674-1



ICS 93.100

Supersedes  
DIN EN 13674-1:2011-04**Railway applications –****Track –****Rail – Part 1: Vignole railway rails 46 kg/m and above;****English version EN 13674-1:2011+A1:2017,****English translation of DIN EN 13674-1:2017-07**

## Bahnanwendungen –

## Oberbau –

Schienen – Teil 1: Vignolschienen ab 46 kg/m;

Englische Fassung EN 13674-1:2011+A1:2017,

Englische Übersetzung von DIN EN 13674-1:2017-07

## Applications ferroviaires –

## Voie –

Rails – Partie 1: Rails Vignole de masse supérieure ou égale à 46 kg/m;

Version anglaise EN 13674-1:2011+A1:2017,

Traduction anglaise de DIN EN 13674-1:2017-07

Document comprises 124 pages

Translation by DIN-Sprachendienst.

In case of doubt, the German-language original shall be considered authoritative.

*A comma is used as the decimal marker.*

## **National foreword**

This document (EN 13674-1:2011+A1:2017) has been prepared by Technical Committee CEN/TC 256 “Railway track products” (Secretariat: DIN, Germany).

The responsible German body involved in its preparation was *DIN-Normenausschuss Eisen und Stahl* (DIN Standards Committee Iron and Steel), Working Committee NA 021-00-12 AA “Railway track products”.

## **Amendments**

This standard differs from DIN EN 13674-1:2011-04 as follows:

- a) rail profile drawings and technical and physical properties have been fundamentally revised;
- b) the rail profile 54E6 has been included;
- c) a new Annex F “Microscopic examination of rail steels using standard diagrams to assess the content of non-metallic inclusions” has been included;
- d) normative references have been updated;
- e) further technical corrections can be found in the updated Annex G, Table G.1;
- f) the standard has been editorially revised.

## **Previous editions**

DIN 5901-1: 1938-01, 1948-03, 1965-03  
DIN 5902-1: 1942-12, 1948-03, 1965-06, 1968-07  
DIN 5901: 1995-11  
DIN EN 13674-1: 2003-12, 2008-01, 2011-04

English Version

## Railway applications - Track - Rail - Part 1: Vignole railway rails 46 kg/m and above

Applications ferroviaires - Voie - Rails - Partie 1: Rails  
Vignole de masse supérieure ou égale à 46 kg/m

Bahnanwendungen - Oberbau - Schienen - Teil 1:  
Vignolschienen ab 46 kg/m

This European Standard was approved by CEN on 10 December 2010 and includes Amendment 1 approved by CEN on 25 December 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG



**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Contents

Page

European foreword.....	5
Introduction .....	7
1 Scope .....	8
2 Normative references .....	8
3 Terms and definitions .....	8
4 Information to be supplied by the purchaser .....	9
5 Steel grades .....	10
6 Profile drawings/properties/mass .....	11
7 Manufacture .....	12
7.1 Product integrity .....	12
7.2 Blooms.....	12
7.3 Rails.....	12
7.4 Identification .....	12
7.4.1 Branding.....	12
7.4.2 Hot stamping.....	13
7.4.3 Cold stamping.....	14
7.4.4 Other identification .....	14
8 Qualifying tests .....	14
8.1 Procedure.....	14
8.2 Fracture toughness ( $K_{IC}$ ).....	15
8.2.1 Test pieces and test methods.....	15
8.2.2 Qualifying criteria.....	15
8.3 Fatigue crack growth rate .....	15
8.3.1 Test method .....	15
8.3.2 Test pieces .....	15
8.3.3 Number of tests and test conditions.....	15
8.3.4 Qualifying criteria.....	15
8.4 Fatigue test .....	16
8.4.1 Test method .....	16
8.4.2 Test pieces .....	16
8.4.3 Number of tests and test conditions.....	16
8.4.4 Qualifying criteria.....	16
8.5 Residual stress in rail foot .....	16
8.5.1 Test method .....	16
8.5.2 Test pieces .....	16
8.5.3 Measurements.....	16
8.5.4 Qualifying criteria.....	16
8.6 Variation of centre line running surface hardness of heat treated rails.....	17
8.7 Tensile strength and elongation .....	17
8.8 Segregation.....	18
8.9 Other qualifying requirements .....	18
9 Acceptance tests .....	18
9.1 Laboratory tests.....	18

9.1.1	General .....	18
9.1.2	Sampling and preparation of samples and test pieces.....	18
9.1.3	Chemical composition.....	18
9.1.4	Microstructure.....	23
9.1.5	Decarburisation .....	24
9.1.6	Oxide cleanness.....	24
9.1.7	Sulfur prints.....	24
9.1.8	Hardness .....	24
9.1.9	Tensile tests.....	25
9.1.10	Retest procedures .....	26
9.2	Dimension tolerances .....	26
9.2.1	Profile .....	26
9.2.2	Straightness, surface flatness and twist .....	27
9.2.3	Cutting and drilling.....	33
9.3	Gauges.....	33
9.4	Inspection for internal quality and surface quality .....	33
9.4.1	Internal quality.....	33
9.4.2	Surface quality .....	36
9.4.3	Checking of automated testing equipment.....	38
Annex A (normative) Rail profiles.....		49
Annex B (normative) Standard test method for the determination of the plane strain fracture toughness ( $K_{IC}$ ) of rails .....		76
B.1	Test methods.....	76
B.2	Test pieces.....	76
B.3	Number of tests .....	76
B.4	Test conditions) .....	76
B.5	Analysis of test data .....	77
B.6	Reporting of results .....	77
Annex C (normative) Method for the determination of rail foot surface longitudinal residual stresses.....		82
C.1	Procedure .....	82
C.2	Strain gauges and their location .....	82
Annex D (normative) Limiting sulfur prints.....		85
Annex E (normative) Profile and drilling gauges.....		99
Annex F (normative) $\text{A}_1$ Microscopic examination of rail steels using standard diagrams to assess the content of non-metallic inclusions $\text{A}_1$ .....		113
F.1	General .....	113
F.1.1	Degree of purity .....	113
F.1.2	Standard diagram plate No. 1 .....	113
F.2	Preparation of specimens.....	113
F.3	Structure and use of standard diagram plate No. 1 .....	113
F.3.1	Use of diagram plate No. 1 .....	113
F.3.2	Rating a single inclusion .....	114
F.3.3	Rating of very small inclusions.....	114
F.4	Test procedure .....	114
F.4.1	Magnification.....	114
F.4.2	Selection of inclusions .....	114
F.5	Evaluation.....	115
F.5.1	General .....	115
F.5.2	Method of evaluation.....	115
F.5.3	Calculation procedure for evaluation using method K .....	115

<b>Annex G (informative) Significant technical changes between this European standard and the previous edition.....</b>	<b>118</b>
<b>Annex ZA (informative)  Relationship between this European Standard and the Essential Requirements of EU Directive 2008/57/EC  .....</b>	<b>120</b>
<b>Bibliography.....</b>	<b>122</b>

## European foreword

This document (EN 13674-1:2011+A1:2017) has been prepared by Technical Committee CEN/TC 256 “Railway applications”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2017, and conflicting national standards shall be withdrawn at the latest by November 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document includes Amendment 1 approved by CEN on 25 December 2016.

This document supersedes A1 EN 13674-1:2011 A1.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

This document has been prepared under a mandate given to CEN/CENELEC/ETSI by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive 2008/57/EC.

For relationship with EU Directive 2008/57/EC, see informative Annex ZA, which is an integral part of this document.

A1 Annex G A1 provides details of significant technical changes between this European Standard and the previous edition.

This part of EN 13674 is the first of the series EN 13674, *Railway applications — Track — Rail*, which consists of the following parts:

- *Part 1: Vignole railway rails 46 kg/m and above;*
- *Part 2: Switch and crossing rails used in conjunction with Vignole railway rails 46 kg/m and above;*
- *Part 3: Check rails;*
- *Part 4: Vignole railway rails from 27 kg/m to, but excluding 46 kg/m.*

Other standards for rails and corresponding welding processes, already published or under preparation, are:

- EN 14587-1, *Railway applications — Track — Flash butt welding of rails — Part 1: New R220, R260, R260Mn and R350HT grade rails in a fixed plant;*
- EN 14587-2, *Railway applications — Track — Flash butt welding of rails — Part 2: New R220, R260, R260Mn and R350HT grade rails by mobile welding machines at sites other than at a fixed plant;*
- prEN 14587-3, *Railway applications — Track — Flash butt welding of rails — — Part 3: Welding in association with crossing construction;*
- EN 14730-1, *Railway applications — Track — Aluminothermic welding of rails — Part 1: Approval of welding processes;*

- EN 14730-2, *Railway applications — Track — Aluminothermic welding of rails — Part 2: Qualification of aluminothermic welders, approval of contractors and acceptance of welds*;
- EN 14811, *Railway applications — Track — Special purpose rail — Grooved and associated construction*;
- EN 15594, *Railway applications — Track — Restoration of rails by electric arc welding*;
- prEN xxxxx, *Railway applications — Track — Forged rail transitions*.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



## **Introduction**

This Introduction provides an explanation of the concepts, and reasoning considered for this standard.

Whenever possible this part of EN 13674 is performance based, recognises the European Quality System standard EN ISO 9001 and requires manufacturers to offer the latest proven technology to consistently satisfy the demanding quality of the required product.

This part of EN 13674 has two major divisions:

- 1) qualifying tests;
- 2) acceptance tests.

The qualifying tests take into account performance requirements. They also include typical results from relevant acceptance tests.

The acceptance tests control those characteristics of the rail steel and rail that are of relevance to the production of high quality rails including heat treated rails and the demands of the railway.

To ensure the supply of high quality rails, some restrictions on production processes are considered.

The performance based standard applies to all procurements falling inside the requirements of the European Procurement Directive (93/38/EEC of 14<sup>th</sup> June 1993), taking into account safety implications and at the same time addressing modern production technology and the requirements of high-speed railways. As a result of the Directive it was recognised that there would be few opportunities (and these would have to be for transparent safety considerations) for derogation from the standard to operate between the user and the manufacturer.

The standard includes a prerequisite for all manufacturers to prove conformity against a set of qualifying test criteria at the time of tendering. The Qualifying tests include all "normal" acceptance test results plus new "type-casting" features such as fracture toughness, fatigue and residual stress. To provide users with the necessary confidence, acceptance limits have been based on results from rail known to have performed well in demanding track installations.

The standard includes a quality assurance and inspection clause as part of product integrity.

In order that quality management systems are consistent across all manufacturers and that users have the best assurance for the consistency of required product quality on this safety critical component of the track, this rail standard recommends that the manufacturers' quality assurance systems are at least equivalent to the requirements of EN ISO 9001. The inclusion of this requirement also reduces the need to incorporate detailed method and calibration descriptions on items such as normal chemical composition determination and the need to define more extensive testing.

## 1 Scope

This European Standard specifies Vignole railway rails of 46 kg/m and greater linear mass, for conventional and high speed railway track usage.

Nine pearlitic steel grades are specified covering a hardness range of 200 HBW to 440 HBW and include non heat treated non alloy steels, non heat treated alloy steels, and heat treated non alloy steels and heat treated alloy steels.

There are 23 rail profiles specified in this standard.

Two classes of rail straightness are specified, differing in requirements for straightness, surface flatness and crown profile. Two classes of profile tolerances are specified.

## 2 Normative references

**[A1]** The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies. **[A1]**

EN 10163-1, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections — Part 1: General requirements*

**[A1]** *deleted text* **[A1]**

CEN/TR 10261, *Iron and steel — Review of available methods of chemical analysis*

EN 10276-1, *Chemical analysis of ferrous materials — Determination of oxygen in steel and iron — Part 1: Sampling and preparation of steel samples for oxygen determination*

EN ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method (ISO 6506-1:2005)*

EN ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1:2009)*

EN ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition (ISO 14284:1996)*

ISO 1099, *Metallic materials — Fatigue testing — Axial force-controlled method*

ISO 4968, *Steel — Macrographic examination by sulfur print (Baumann method)*

ISO 12108, *Metallic materials — Fatigue testing — Fatigue crack growth method*

ASTM E399, *Standard test method for linear-elastic plane-strain fracture toughness  $K_{Ic}$  of metallic materials*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1 heat

liquid steel melt tapped out of a converter or electric arc furnace which includes after continuous casting a given number of blooms relating to the weight of the heat and the extension of the mixing zone. In the case of sequence casting the blooms belonging to the mixing zone should be clearly defined